

RILSAN® BESNO P40 TL

PA11-P, EHL, 22-003

Rilsan® BESNO P40 TL树脂 是一种采用可再生材料制成的聚酰胺11。该本色牌号经过增塑，适用于挤出。
依据ASTM D 6866，可再生碳含量为 89%。

性能	干 / 已调节	单位	测试标准
机械性能			
拉伸模量	- / 345	MPa	ISO 527-1/-2
	- / 50000	psi	
屈服应力	- / 26	MPa	ISO 527-1/-2
	- / 3770	psi	
屈服伸长率	- / 50	%	ISO 527-1/-2
名义断裂伸长率	- / >50	%	ISO 527-1/-2
肖氏硬度D, 15 s	60 / *	-	ISO 868
简支梁冲击强度, +23°C	- / 无断裂	kJ/m ²	ISO 179/1eU
简支梁冲击强度, -30°C	- / 无断裂	kJ/m ²	ISO 179/1eU
简支梁缺口冲击强度, +23°C	- / 无断裂	kJ/m ²	ISO 179/1eA
简支梁缺口冲击强度, -30°C	- / 7	kJ/m ²	ISO 179/1eA
	- / 3.33	ftlb/in ²	
冲孔最大力, -30°C	- / 6000	N	ISO 6603-2
冲孔功, -30°C	- / 70	J	ISO 6603-2
热性能			
熔融温度, 10°C/min	181 / *	°C	ISO 11357-1/-3
热变形温度, 1.80 MPa	45 / *	°C	ISO 75-1/-2
	113 / *	°F	
热变形温度, 0.45 MPa	130 / *	°C	ISO 75-1/-2
	266 / *	°F	
维卡软化温度, 50°C/h 50N	140 / *	°C	ISO 306
	284 / *	°F	
线性热膨胀系数, 平行	110 / *	E-6/K	ISO 11359-1/-2
电性能			
相对介电常数, 100Hz	9 / -	-	IEC 60250
相对介电常数, 1MHz	4 / -	-	IEC 60250
介质损耗因子, 100Hz	2440 / -	E-4	IEC 60250
介质损耗因子, 1MHz	1040 / -	E-4	IEC 60250
体积电阻率	- / 1E9	Ohm* m	IEC 62631-3-1
表面电阻率	* / 5E11	Ohm	IEC 62631-3-2

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 12-08-2024

RILSAN® BESNO P40 TL

介电强度	- / 23 - / 584	kV/m kV/in	IEC 60243-1
其它性能			
%Bio-Based	89	-	ASTM D6866
吸水性, 23°C, immersion, equilibrium	1.6 / *	%	ISO 62
密度	1040 / 1040 1.04 / 1.04	kg/m ³ g/cm ³	ISO 1183

主要应用

- 流体运输
- 燃料管线
- 机动车用管路
- 气闸线路

包装


该牌号的供货规格为干燥型密封包装（25公斤袋装、44磅袋装、550公斤硬质容器、1000磅硬质容器），可以随时加工处理。

保质期


自发货之日起2年。有关过期使用的任何事宜，请咨询我司技术服务人员。

图表

粘度 - 剪切速度




剪切应力 - 剪切速度




RILSAN® BESNO P40 TL


动态剪切模量 - 温度




应力 - 应变



正割模量 - 应变




应力 - 应变(等时的) 73°F




Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 12-08-2024

RILSAN® BESNO P40 TL


蠕变模量 - 时间. 73°F




应力 - 应变(等时的) 212°F



蠕变模量 - 时间. 212°F



比容 - 温度(PVT)



加工条件：

—推荐熔融温度（最小值/建议值/最大值）：230°C/250°C/280°C.

—干燥时间和温度（只有包装袋打开2小时以上时才有必要干燥）：4-8 小时，80-90°C。

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 12-08-2024

RILSAN[®]

BESNO P40 TL

加工方法 异型材挤出成型, 其它挤出成型	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
供货形式 粒料	
添加剂 润滑剂, 增塑剂	
特殊性能 生物基, 热稳定, 光稳定	
地区供应 北美, 欧洲, 亚太, 中南美洲, 中东/非洲	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

Arkema France - A French "société anonyme", registered in the Nanterre (France)
Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 12-08-2024