

KYNAR SUPERFLEX[®]

2500-20

Kynar Superflex[®]树脂 是一种热塑性塑料氟化聚合物。
其特性与标准牌号相同：耐化学腐蚀性、耐紫外线性、低渗透性、高纯度、优异的机械特性。
此外，该柔韧性非常好，适用于电气隔离线缆、管路和共挤。
该牌号的供应形态为球状颗粒，适用于注塑、挤出、模压成型工艺。

性能	价值	单位	测试标准
流变性能			
熔体体积流动速度	5.8	cm ³ /10min	ISO 1133
温度	232	°C	-
	450	°F	-
载荷	3.8	kg	-
	8.38	lb	-
熔融指数	1 - 15	g/10min	ASTM D1238
温度	230	°C	-
负载	3.8	kg	-
熔体粘度, 230°C, 100 s ⁻¹	9 - 16	kPoise	ASTM D3835
机械性能			
拉伸模量	350	MPa	ISO 527-1/-2
	50800	psi	
拉伸模量, 73 °F	241 - 379	MPa	ASTM D638
	35000 - 55000	psi	
屈服应力	15	MPa	ISO 527-1/-2
	2180	psi	
屈服应力, 73 °F	11.7 - 19.3	MPa	ASTM D638
	1700 - 2800	psi	
屈服伸长率	18	%	ISO 527-1/-2
屈服伸长率, 73 °F	17 - 25	%	ASTM D638
名义断裂伸长率	>50	%	ISO 527-1/-2
断裂拉伸强度, 73 °F	13.8 - 31	MPa	ASTM D638
	2000 - 4500	psi	
断裂伸长率, 73 °F	300 - 400	%	ASTM D638
TABER耐磨耗性, CS 17 1000g:pad	28 - 33	mg/100 cycles	ASTM-G195-13A
肖氏硬度, D, 73 °F	50 - 57	-	ASTM D2240
弯曲模量, 73 °F	193 - 276	MPa	ASTM D790
	28000 - 40000	psi	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR SUPERFLEX[®]

2500-20

5%伸长率时弯曲强度, 73 °F	10.3 - 17.2	MPa	ASTM D790
	1500 - 2500	psi	
压缩强度, 73 °F	13.8 - 20.7	MPa	ASTM D695
	2000 - 3000	psi	
简支梁缺口冲击强度, +23°C	无断裂	kJ/m ²	ISO 179/1eA
冲击强度, 73 °F	无断裂	kJ/m	ASTM D256
梁缺口冲击强度, 73 °F	无断裂	kJ/m	ASTM D256
摩擦系数, 静态vs.钢, 73°F	0.49	-	ASTM D1894
摩擦系数, 动态vs.钢, 73°F	0.54	-	ASTM D1894
热性能			
熔融温度, 10°C/min	122	°C	ISO 11357-1/-3
熔点	117 - 125	°C	ASTM D3418
玻璃化转变温度, 10°C/min	-40	°C	ISO 11357-1/-2
玻璃化转变温度 (Tg)	-43.3 - -40	°C	ASTM D7028
	-46 - -40	°F	
热变形温度, 1.80 MPa	31	°C	ISO 75-1/-2
	88	°F	
热变形温度, 264 Psi, 248 °F/hr	26.7 - 37.8	°C	ASTM D648
	80 - 100	°F	
热释放速率, 73 °F	15.3 - 19.4	10E-5/ °C	ASTM D696
	8.5 - 10.8	10E-5/ °F	
阻燃等级, 1.5mm厚	V-0	class	IEC 60695-11-10
测试用试样的厚度	1.5	mm	-
	0.0591	in	
Yellow Card 现存	是的	-	-
阻燃等级, 厚度h	V-0	class	IEC 60695-11-10
测试用试样的厚度	1.0	mm	-
	0.0394	in	
氧指数	44	%	ISO 4589-1/-2
氧指数	42	%	ASTM D2863
热导率	0.144 - 0.18	W/(m K)	ASTM D433
	1 - 1.25	BTU in (hr ft ² °F)	
比热	745 - 958	J/(kg K)	DSC
	0.28 - 0.36	BTU/(l b °F)	
在空气中热分解	375	°C	1% wt. loss
	707	°F	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR SUPERFLEX[®]

2500-20

在氮气中热分解	410 770	°C °F	1% wt. loss
电性能			
电介质常数, 1 kHz	4.5 - 13.5	-	ASTM D150
耗散因素, 100 kHz	0.05 - 0.29	-	ASTM D150
体积电阻率, DC 68 °F, 65% R.H.	2E14	Ohm* cm	ASTM D257
表面电阻率, 73 °F	8.5E11 - 9.2E11	Ohm per square	ASTM D257
介电强度	12 305	kV/m kV/in	IEC 60243-1
电介质强度, 73°F	0.8 - 1.1	kV/mil	ASTM D149
其它性能			
吸水性, 23°C, immersion, equilibrium	0.03	%	ISO 62
吸水性	≤ 0.07	%	ASTM D570
密度	1790 1.79	kg/m ³ g/cm ³	ISO 1183
比重, 73 °F	1.8 - 1.82	-	ASTM D792
光学特性			
Refractive Index @ sodium D line	1.4	-	ASTM D542

加工方法	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
注塑, 片材挤出成型, 涂覆, 传递模塑成型	
供货形式	
粒料	
特殊性能	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
热稳定, 光稳定	
地区供应	
北美, 欧洲, 亚太, 中南美洲, 中东/非洲	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.