

KYNAR® 1000 HD

Kynar® resins are fluorinated thermoplastic homopolymers.

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo mechanical properties.

Kynar® 1000 HD resin is a standard grade of granules for compression and transfer molding, for extrusion of thick walled parts: blocks, rods, plaques, tubes.

[UL Yellow Card](#)

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	1.1	cm ³ /10 min	ISO 1133
Temperature	230	°C	-
	446	°F	-
Load	5	kg	-
	11	lb	-
Melt Flow Rate	1 - 3	g/10min	ASTM D1238
Temperature	230	°C	-
Load	5	kg	-
Molding Shrinkage, parallel	2.0	%	ISO 294-4, 2577
Molding Shrinkage, normal	2.0	%	ISO 294-4, 2577
Melt Viscosity, 230°C, 100 s ⁻¹	15 - 20	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus	2000	MPa	ISO 527-1/-2
	290000	psi	
Yield Stress	50	MPa	ISO 527-1/-2
	7250	psi	
Tensile Strength at Yield, 73 °F	44.8 - 55.2	MPa	ASTM D638
	6500 - 8000	psi	
Yield Strain	9	%	ISO 527-1/-2
Nominal Strain at Break	>50	%	ISO 527-1/-2
Tensile Strength at Break, 73 °F	34.5 - 55.2	MPa	ASTM D638
	5000 - 8000	psi	
Elongation at Break, 73 °F	20 - 100	%	ASTM D638
Hardness, Shore D, 73 °F	76 - 80	-	ASTM D2240
Flexural Modulus, 73 °F	1450 - 2310	MPa	ASTM D790
	210000 - 335000	psi	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

KYNAR® 1000 HD

Compressive Strength, 73 °F	68.9 - 103	MPa	ASTM D695
	10000 - 15000	psi	
Charpy Impact Strength, +23°C	No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	22	kJ/m ²	ISO 179/1eA
	10.5	ftlb/in ²	
Charpy Notched Impact Strength, -30°C	5	kJ/m ²	ISO 179/1eA
	2.38	ftlb/in ²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	169	°C	ISO 11357-1/-3
Melting Point	172	°C	ASTM D3418
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Glass Transition Temperature (Tg)	-40	°C	ASTM D7028
Temperature Rating	150	°C	UL RTI
	302	°F	
Temp. of Deflection Under Load, 1.80 MPa	104	°C	ISO 75-1/-2
	219	°F	
Heat Deflection Temperature, 264 Psi, 248 °F/hr	105 - 115	°C	ASTM D648
	221 - 239	°F	
Heat Deflection Temperature, 66 Psi, 248 °F/hr	125 - 140	°C	ASTM D648
	257 - 284	°F	
Vicat Softening Temperature, 50°C/h 50N	138	°C	ISO 306
	280	°F	
Coeff. of Linear Thermal Expansion, parallel	150	E-6/K	ISO 11359-1/-2
Coefficient of Thermal Expansion, 73 °F	11.9 - 14.4	10E-5/ °C	ASTM D696
	6.6 - 8	10E-5/ °F	
Burning Behav. at 1.5 mm Nominal Thickness	V-0	class	IEC 60695-11-10
Thickness Tested	1.6	mm	-
	0.0630	in	
Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
Thickness Tested	0.8	mm	-
	0.0315	in	
Oxygen Index	83	%	ISO 4589-1/-2
Limiting Oxygen Index	60	%	ASTM D2863
Thermal Conductivity	0.17 - 0.19	W/(m K)	ASTM D433
	1.18 - 1.32	BTU in /(hr ft ² F)	

Arkema France - A French "société anonyme", registered in the Nanterre (France)
 Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

KYNAR® 1000 HD

Specific Heat	745 - 958 0.28 - 0.36	J/(kg K) BTU/(l b·°F)	DSC
Thermal Decomposition TGA, in air	375 707	°C °F	1% wt. loss
Thermal Decomposition TGA, in nitrogen	410 770	°C °F	1% wt. loss
Relative Thermal Index, Mechanical	150 302	°C °F	UL 746B
Relative Thermal Index, Electrical	150 302	°C °F	UL 746B
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	10.5	-	IEC 60250
Relative Permittivity, 1MHz	7	-	IEC 60250
Dissipation Factor, 100Hz	270	E-4	IEC 60250
Dissipation Factor, 1MHz	2400	E-4	IEC 60250
Volume Resistivity	2.3E10	Ohm* m	IEC 62631-3-1
Volume Resistivity, DC 68 °F, 65% R.H.	2E14	Ohm*c m	ASTM D257
Surface Resistivity	4E13	Ohm	IEC 62631-3-2
Dielectric (Electric) Strength	27	kV/mm	IEC 60243-1
	686	kV/in	
Comparative Tracking Index	600	-	IEC 60112
OTHER PROPERTIES			
Water Absorption, 23°C, immersion, equilibrium	0.03	%	ISO 62
Water Absorption	0.01 - 0.03	%	ASTM D570
Humidity Absorption, 23°C, RH50%, equilibrium	0.015	%	ISO 62
Density	1770	kg/m ³	ISO 1183
	1.77	g/cm ³	
Specific Gravity, 73 °F	1.77 - 1.79	-	ASTM D792
OPTICAL PROPERTIES			
Refractive Index @ sodium D line	1.42	-	ASTM D542

MAIN APPLICATIONS:

- corrosion protection in the chemical industry
- coating (painting, co-extrusion)
- off shore
- wire and cable

KYNAR[®]

1000 HD

<p>PROCESSING</p> <p>Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion, Blow Molding, Transfer Molding, Thermoforming</p>	<p>Headquarters:</p> <p>Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France</p>
<p>DELIVERY FORM</p> <p>Pellets</p>	<p>T +33 (0)1 49 00 80 80 hpp.arkema.com</p>
<p>REGIONAL AVAILABILITY</p> <p>North America, Europe, Asia Pacific, South and Central America, Near East/Africa</p>	<p>Arkema Inc. – High Performance Polymers</p> <p>900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000</p>
	<p>hpp.arkema.com</p>

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.