

KYNAR FLEX®

3030-15

Kynar Flex® 3030-15 resin is a copolymer of vinylidene fluoride and hexafluoropropylene specifically designed for flexible plenum cables and tubing.

Its main characteristics are:

- Very high flexibility
- High melting point
- Excellent low temperature impact resistance
- Plenum rated

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Flow Rate	8 - 25	g/10min	ASTM D1238
Temperature	230	°C	-
Load	3.8	kg	-
Melt Viscosity, 230°C, 100 s ⁻¹	7 - 13	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus	290 42100	MPa psi	ISO 527-1/-2
Tensile Modulus, 73 °F	207 - 345 30000 - 50000	MPa psi	ASTM D638
Yield Stress	12 1740	MPa psi	ISO 527-1/-2
Tensile Strength at Yield, 73 °F	12.4 - 16.5 1800 - 2400	MPa psi	ASTM D638
Yield Strain	30	%	ISO 527-1/-2
Elongation at Yield, 73 °F	25 - 40	%	ASTM D638
Nominal Strain at Break	>50	%	ISO 527-1/-2
Tensile Strength at Break, 73 °F	19.3 - 24.8 2800 - 3600	MPa psi	ASTM D638
Elongation at Break, 73 °F	≥500	%	ASTM D638
Taber Abrasion, CS 17 1000g:pad	28 - 33	mg/1000 cycles	ASTM-G195-13A
Hardness, Shore D, 73 °F	45 - 55	-	ASTM D2240
Flexural Modulus, 73 °F	241 - 379 35000 - 55000	MPa psi	ASTM D790
Charpy Notched Impact Strength, +23°C	No Break	kJ/m ²	ISO 179/1eA
Notched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
THERMAL PROPERTIES			

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

KYNAR FLEX[®]

3030-15

Melting Temperature, 10°C/min	164	°C	ISO 11357-1/-3
Melting Point	160 - 168	°C	ASTM D3418
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Glass Transition Temperature (Tg)	-40	°C	ASTM D7028
Coefficient of Thermal Expansion, 73 °F	15.3 - 19.4	10E-5/	ASTM D696
	8.5 - 10.8	°C 10E-5/	
Burning Behav. at Thickness h	V-0	°F class	IEC 60695-11-10
Thickness Tested	0.8	mm	-
	0.0315	in	
Oxygen Index	90	%	ISO 4589-1/-2
Limiting Oxygen Index	≥75	%	ASTM D2863
ELECTRICAL PROPERTIES			
Volume Resistivity	2E12	Ohm* m	IEC 62631-3-1
Surface Resistivity, 73 °F	7.6E11 - 7.9E11	Ohm per square	ASTM D257
Dielectric (Electric) Strength, 73°F	1 - 1.2	kV/mil	ASTM D149
OTHER PROPERTIES			
Water Absorption	≤0.05	%	ASTM D570
Specific Gravity, 73 °F	1.78 - 1.82	-	ASTM D792

REGIONAL AVAILABILITY	Headquarters:
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.