

KYNAR FLEX®

3120-15

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® 3120-15 resin has been specifically designed for use in wire and cable constructions which require a 150°C rating and improve flame and smoke resistance.

Kynar Flex® 3120-15 resin is easily processed and has excellent physical, mechanical, thermal and flame resistant characteristics. Its low viscosity allows easy processing.

Additional Characteristics:

- Excellent thermal stability
- Excellent abrasion resistance
- High Limiting Oxygen Index
- Extremely low smoke emission characteristics

Kynar Flex® 3120-15 resin meets the smoke and flame requirements of UL 910.

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	4	cm ³ /10 min	ISO 1133
Temperature	232	°C	-
	450	°F	-
Load	3.8	kg	-
	8.38	lb	-
Melt Flow Rate	4 - 18	g/10min	ASTM D1238
Temperature	230	°C	-
	3.8	kg	-
Load	3.8	kg	-
	6 - 12	kPoise	ASTM D3835
Melt Viscosity, 230°C, 100 s ⁻¹	6 - 12	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus	700	MPa	ISO 527-1/-2
	102000	psi	
Tensile Modulus, 73 °F	689 - 1170	MPa	ASTM D638
	100000 - 170000	psi	
Yield Stress	27	MPa	ISO 527-1/-2
	3920	psi	
Tensile Strength at Yield, 73 °F	24.1 - 34.5	MPa	ASTM D638
	3500 - 5000	psi	
Yield Strain	15	%	ISO 527-1/-2
Elongation at Yield, 73 °F	10 - 20	%	ASTM D638
Nominal Strain at Break	>50	%	ISO 527-1/-2

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 12-08-2024

KYNAR FLEX[®]

3120-15

Tensile Strength at Break, 73 °F	34.5 - 48.3	MPa	ASTM D638
	5000 - 7000	psi	
Elongation at Break, 73 °F	300 - 500	%	ASTM D638
Taber Abrasion, CS 17 1000g:pad	16 - 19	mg/1000 cycles	ASTM-G195-13A
Hardness, Shore D, 73 °F	65 - 70	-	ASTM D2240
Flexural Modulus, 73 °F	621 - 827	MPa	ASTM D790
	90000 - 120000	psi	
Flexural Strength @ 5% Strain, 73 °F	20.7 - 34.5	MPa	ASTM D790
	3000 - 5000	psi	
Compressive Strength, 73 °F	31 - 41.4	MPa	ASTM D695
	4500 - 6000	psi	
Charpy Notched Impact Strength, +23°C	No Break	kJ/m ²	ISO 179/1eA
Unnotched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
Notched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
Coefficient of Friction, Static vs. Steel, 73 °F	0.31	-	ASTM D1894
Coefficient of Friction, Dynamic vs. Steel, 73 °F	0.3	-	ASTM D1894
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	164	°C	ISO 11357-1/-3
Melting Point	161 - 168	°C	ASTM D3418
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Glass Transition Temperature (Tg)	-41.1 - -39.4	°C	ASTM D7028
	-42 - -39	°F	
Temperature Rating	150	°C	UL RTI
	302	°F	
Temp. of Deflection Under Load, 1.80 MPa	48	°C	ISO 75-1/-2
	119	°F	
Heat Deflection Temperature, 264 Psi, 248 °F/hr	43.3 - 54.4	°C	ASTM D648
	110 - 130	°F	
Temp. of Deflection Under Load, 0.45 MPa	65	°C	ISO 75-1/-2
	149	°F	
Heat Deflection Temperature, 66 Psi, 248 °F/hr	54.4 - 76.7	°C	ASTM D648
	130 - 170	°F	
Coefficient of Thermal Expansion, 73 °F	12.6 - 18.5	10E-5/°C	ASTM D696
	7 - 10.3	10E-5/°F	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

KYNAR FLEX[®]

3120-15

Burning Behav. at 1.5 mm Nominal Thickness	V-0	class	IEC 60695-11-10
Thickness Tested	1.5	mm	-
	0.0591	in	
Yellow Card available	yes	-	-
Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
Thickness Tested	1.0	mm	-
	0.0394	in	
Oxygen Index	95	%	ISO 4589-1/-2
Limiting Oxygen Index	95	%	ASTM D2863
Thermal Conductivity	0.144 - 0.18	W/(m	ASTM D433
	1 - 1.25	K)	
		BTU in	
Specific Heat	745 - 958	J/(kg	DSC
		F)	
	0.28 - 0.36	BTU/(l	
		b °C	
Thermal Decomposition TGA, in air	375	°C	1% wt. loss
	707	°F	
Thermal Decomposition TGA, in nitrogen	410	°C	1% wt. loss
	770	°F	
Relative Thermal Index, Mechanical	150	°C	UL 746B
	302	°F	
Relative Thermal Index, Electrical	150	°C	UL 746B
	302	°F	
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	6.7	-	IEC 60250
Dielectric Constant, 1 kHz	3.2 - 10.2	-	ASTM D150
Dissipation Factor, 100Hz	0.105	E-4	IEC 60250
Dissipation Factor, 100 kHz	0.02 - 0.19	-	ASTM D150
Volume Resistivity	2E12	Ohm*	IEC 62631-3-1
		m	
Surface Resistivity, 73 °F	5.9E11 - 6.1E11	Ohm	ASTM D257
		per	
		square	
Dielectric (Electric) Strength, 73°F	1.3 - 1.5	kV/mil	ASTM D149
OTHER PROPERTIES			
Water Absorption	0.03 - 0.05	%	ASTM D570
Density	1780	kg/m ³	ISO 1183
	1.78	g/cm ³	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

KYNAR FLEX®

3120-15

Specific Gravity, 73 °F

1.77 - 1.8

-

ASTM D792

<p>PROCESSING</p> <p>Other Extrusion</p>	<p>Headquarters:</p> <p>Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com</p> <p>Arkema Inc. – High Performance Polymers</p> <p>900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com</p>
<p>DELIVERY FORM</p> <p>Pellets</p>	
<p>ADDITIVES</p> <p>Lubricants</p>	
<p>SPECIAL CHARACTERISTICS</p> <p>Heat Stabilized, Light Stabilized</p>	
<p>REGIONAL AVAILABILITY</p> <p>North America, Europe, Asia Pacific, South and Central America, Near East/Africa</p>	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024