

# KYNAR FLEX®

## 3120-50

[Kynar Flex®](#) resins are fluorinated thermoplastic copolymers.

**Kynar Flex® 3120-50** is a pelletized flexible, semi-crystalline VF2 based copolymer. It can be molded or extruded and has a useful temperature range from -40°C - 150°C. Kynar Flex® 3120-50 has a UL RTI of 150°C. This product is **NSF/ANSI/CAN 61** certified.

Kynar Flex® 3120-50 can be used in compounding for cross-linkable wire and cable as well as both wire applications requiring low temperature flexibility and high temperature resistance.

Kynar Flex® 3120-50 also finds use as a polymer processing aid (PPA) for polyolefins. The use of Kynar Flex® 3120-50 or Kynar Flex 3121-50 at 200 -1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

### [UL Yellow Card](#)

PROPERTIES	VALUE	UNIT	TEST STANDARD
<b>RHEOLOGICAL PROPERTIES</b>			
Melt Volume-Flow Rate	0.5	cm <sup>3</sup> /10 min	ISO 1133
Temperature	230	°C	-
	446	°F	-
Load	12.5	kg	-
	27.6	lb	-
Melt Flow Rate	2.5 - 7.5	g/10min	ASTM D1238
Temperature	230	°C	-
Load	12.5	kg	-
Melt Viscosity, 230°C, 100 s <sup>-1</sup>	20 - 26	kPoise	ASTM D3835
<b>MECHANICAL PROPERTIES</b>			
Tensile Modulus	700	MPa	ISO 527-1/-2
	102000	psi	
Tensile Modulus, 73 °F	689 - 1170	MPa	ASTM D638
	100000 - 170000	psi	
Yield Stress	27	MPa	ISO 527-1/-2
	3920	psi	
Tensile Strength at Yield, 73 °F	24.1 - 34.5	MPa	ASTM D638
	3500 - 5000	psi	
Yield Strain	15	%	ISO 527-1/-2
Elongation at Yield, 73 °F	10 - 20	%	ASTM D638
Nominal Strain at Break	>50	%	ISO 527-1/-2
Tensile Strength at Break, 73 °F	34.5 - 48.3	MPa	ASTM D638
	5000 - 7000	psi	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018  
Source: automatically generated TDS from Material Database on 12-08-2024

# KYNAR FLEX<sup>®</sup>

## 3120-50

Elongation at Break, 73 °F	100 - 200	%	ASTM D638
Taber Abrasion, CS 17 1000g:pad	16 - 19	mg/1000 cycles	ASTM-G195-13A
Hardness, Shore D, 73 °F	65 - 70	-	ASTM D2240
Flexural Modulus, 73 °F	621 - 827	MPa	ASTM D790
	90000 - 120000	psi	
Flexural Strength @ 5% Strain, 73 °F	20.7 - 34.5	MPa	ASTM D790
	3000 - 5000	psi	
Compressive Strength, 73 °F	31 - 41.4	MPa	ASTM D695
	4500 - 6000	psi	
Charpy Notched Impact Strength, +23°C	No Break	kJ/m <sup>2</sup>	ISO 179/1eA
Unnotched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
Notched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
Coefficient of Friction, Static vs. Steel, 73 °F	0.31	-	ASTM D1894
Coefficient of Friction, Dynamic vs. Steel, 73 °F	0.3	-	ASTM D1894
<b>THERMAL PROPERTIES</b>			
Melting Temperature, 10°C/min	165	°C	ISO 11357-1/-3
Melting Point	161 - 168	°C	ASTM D3418
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Glass Transition Temperature (Tg)	-41.1 - -39.4	°C	ASTM D7028
	-42 - -39	°F	
Temperature Rating	150	°C	UL RTI
	302	°F	
Temp. of Deflection Under Load, 1.80 MPa	50	°C	ISO 75-1/-2
	122	°F	
Heat Deflection Temperature, 264 Psi, 248 °F/hr	43.3 - 54.4	°C	ASTM D648
	110 - 130	°F	
Heat Deflection Temperature, 66 Psi, 248 °F/hr	54.4 - 76.7	°C	ASTM D648
	130 - 170	°F	
Coefficient of Thermal Expansion, 73 °F	12.6 - 18.5	10E-5/ °C	ASTM D696
	7 - 10.3	10E-5/ °F	
Burning Behav. at 1.5 mm Nominal Thickness	V-0	class	IEC 60695-11-10
Thickness Tested	1.5	mm	-
	0.0591	in	
Yellow Card available	yes	-	-

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018  
 Source: automatically generated TDS from Material Database on 12-08-2024

# KYNAR FLEX<sup>®</sup>

## 3120-50

Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
Thickness Tested	1.0	mm	-
	0.0394	in	
Yellow Card available	yes	-	-
Burning Behav. 5V at Thickness h	5VA	class	IEC 60695-11-20
Thickness Tested	1.0	mm	-
	0.0394	in	
Oxygen Index	43	%	ISO 4589-1/-2
Limiting Oxygen Index	42	%	ASTM D2863
Thermal Conductivity	0.144 - 0.18	W/(m	ASTM D433
	1 - 1.25	K)	
Specific Heat	745 - 958	BTU in	DSC
	0.28 - 0.36	/(hr ft <sup>2</sup>	
Thermal Decomposition TGA, in air	375	K)	
	707	°C	1% wt. loss
Thermal Decomposition TGA, in nitrogen	410	°C	1% wt. loss
	770	°F	
Relative Thermal Index, Mechanical	150	°C	UL 746B
	302	°F	
Relative Thermal Index, Electrical	150	°C	UL 746B
	302	°F	
<b>ELECTRICAL PROPERTIES</b>			
Dielectric Constant, 1 kHz	3.2 - 10.2	-	ASTM D150
Dissipation Factor, 100 kHz	0.02 - 0.19	-	ASTM D150
Surface Resistivity, 73 °F	5.3E11 - 5.5E11	Ohm	ASTM D257
		per	
		square	
Dielectric (Electric) Strength, 73°F	1.3 - 1.5	kV/mil	ASTM D149
<b>OTHER PROPERTIES</b>			
Water Absorption, 23°C, immersion, equilibrium	0.03	%	ISO 62
Water Absorption	0.03 - 0.05	%	ASTM D570
Density	1780	kg/m <sup>3</sup>	ISO 1183
	1.78	g/cm <sup>3</sup>	
Specific Gravity, 73 °F	1.75 - 1.77	-	ASTM D792
<b>OPTICAL PROPERTIES</b>			
Refractive Index @ sodium D line	1.41	-	ASTM D542

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018  
 Source: automatically generated TDS from Material Database on 12-08-2024

# KYNAR FLEX<sup>®</sup>

## 3120-50

<b>PROCESSING</b> Profile Extrusion, Other Extrusion	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com  Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
<b>DELIVERY FORM</b> Pellets	
<b>SPECIAL CHARACTERISTICS</b> Heat Stabilized, Light Stabilized	
<b>REGIONAL AVAILABILITY</b> North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

Arkema France - A French "société anonyme", registered in the Nanterre (France)  
Trade and Companies Register under the number 319 632 790 SDC/11-2018  
Source: automatically generated TDS from Material Database on 12-08-2024