

KYNAR FLEX® LBG

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® LBG resin is a semi-crystalline copolymer. Kynar Flex® LBG is considered a high molecular weight VF₂ based copolymers - specifically designed for application in the lithium ion battery market.

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	3.2	cm ³ /10 min	ISO 1133
Temperature	232	°C	-
	450	°F	-
Load	21.6	kg	-
	47.6	lb	-
Melt Flow Rate	3 - 8	g/10min	ASTM D1238
Temperature	230	°C	-
Load	21.6	kg	-
Melt Viscosity, 230°C, 100 s ⁻¹	34 - 38	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Yield Stress	35	MPa	ISO 527-1/-2
	5080	psi	
Tensile Strength at Yield, 73 °F	35	MPa	ASTM D638
	5080	psi	
Yield Strain	10	%	ISO 527-1/-2
Nominal Strain at Break	>50	%	ISO 527-1/-2
Elongation at Break, 73 °F	≥400	%	ASTM D638
Flexural Modulus, 73 °F	1030	MPa	ASTM D790
	150000	psi	
Charpy Notched Impact Strength, +23°C	No Break	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	154	°C	ISO 11357-1/-3
Melting Point	151 - 157	°C	ASTM D3418
OTHER PROPERTIES			
Water Absorption, 23°C, immersion, equilibrium	0.03	%	ISO 62
Density	1780	kg/m ³	ISO 1183
	1.78	g/cm ³	
Specific Gravity, 73 °F	1.78	-	ASTM D792

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX[®]

LBG

DELIVERY FORM	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
Powder	
REGIONAL AVAILABILITY	
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.