

# ORGALLOY®

## RDG 113

Orgalloy® RDG 113 resin is a polyamide designed to be used for refrigerant barrier layer in air conditioning rubber hose.

### Packaging:

This grade is delivered dried in sealed packaging (20kg bags) ready to be processed.

### Shelf life:

Two years from the date of delivery. For any use above this limit, please refer to our technical services.s.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
<b>MECHANICAL PROPERTIES</b>			
Tensile Modulus	- / 2253	MPa	ISO 527-1/-2
	- / 327000	psi	
Yield Stress	- / 47	MPa	ISO 527-1/-2
	- / 6820	psi	
Yield Strain	- / 4.4	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
<b>THERMAL PROPERTIES</b>			
Melting Temperature, 10°C/min	229 / *	°C	ISO 11357-1/-3
<b>OTHER PROPERTIES</b>			
Density	1120 / 1120	kg/m³	ISO 1183
	1.12 / 1.12	g/cm³	

### Processing conditions:

- Drying time (only necessary for bags opened for more than two hours): 4-8 hours at 80-90°C
- Extrusion melt temperature (min-recommended-max): 240-260-300°C

<b>PROCESSING</b>	<b>Headquarters:</b>  Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
Other Extrusion	
<b>DELIVERY FORM</b>	
Pellets	Arkema Inc. – High Performance Polymers  900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
<b>REGIONAL AVAILABILITY</b>	
North America, Europe, Asia Pacific, South and Central America	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018  
Source: automatically generated TDS from Material Database on 20-02-2024