

ORGASOL® 2002 ES6 NAT 3 is spheroidal polyamide 12 powder with a narrow particle size distribution and an average diameter of 60µm.

ORGASOL® 2002 ES6 NAT 3 has a melting temperature of 177°C. An extremely high level of quality is achieved through rigorous control of the particle size distribution & porosity, ensuring excellent consistency of performance.

ORGASOL® is a range of high performance ultra-fine polyamide powders used as multifunctional additives in coatings, inks, varnishes and technical compounds.

The introduction of ORGASOL® polyamide powders in formulations is easy thanks to their good dispersion capacity, their reduced Impact on rheology and their low density.

ORGASOL® polyamide powders are surface modifiers, specifically designed for gloss control, texture creation and haptic properties adjustment. They also improve blocking resistance and reduce coefficient of friction.

Abrasion, scratch, impact resistances and flexibility of coatings, inks and varnishes and technical compounds can be significantly improved using ORGASOL® polyamide powders.

POWDER PROPERTIES	VALUE	UNIT	TEST STANDARD
Appearance	White spheroidal powder	-	Visual
	≤ 40µm	10	%
Particle Size Distribution	≥ 80µm	5	%
	Median Size	60	µm
		0.00236	in

APPLICATION PROPERTIES

- **Texturing agent (smooth texture)** Texture depends on amount of Orgasol® polyamide powder, dry coating thickness and conditions of curing.
- **Abrasion & Scratch resistance improvement** reinforces the mechanical properties of the coating
- **Anti-slippery additive** Increased roughness of the coating and easily cleanable surface
- **Compatible with most resins used in coating industry** suitable for solvent-based, water-based and 100% solid UV-curable systems

MAIN APPLICATIONS:

- Coil coating
- Floor coating
- Wood coating
- Plastic coating

PACKAGING

This grade is delivered in 20kg bag.

SHELF LIFE

3 years from date of delivery in closed original packaging away from heat and moisture. For any use after this limit, please refer to our technical services.

DELIVERY FORM Powder	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.