

RILSAN® BECV BLUE T8L

PA11, KHL, 18-010

Rilsan® BECV BLUE T8L resin is a polyamide 11 produced from a renewable source. This blue coloured grade is designed for cable coating but is also suitable for extrusion.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Yield Stress	- / 40	MPa	ISO 527-1/-2
	- / 5800	psi	
Yield Strain	- / 7	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness, after 15 s	71 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / 10	kJ/m²	ISO 179/1eA
	- / 4.76	ftlb/in²	
Charpy Notched Impact Strength, -30°C	- / 12	kJ/m²	ISO 179/1eA
	- / 5.71	ftlb/in²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	189 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1030 / 1030	kg/m³	ISO 1183
	1.03 / 1.03	g/cm³	

MAIN APPLICATIONS:

- Wire and cable sheathing
- Anti-rodent cables

PACKAGING:

This grade is delivered dried in sealed packaging (550 kg rigid containers) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 250°C / 260°C / 270°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 80-90°C.

RILSAN[®]

BECV BLUE T8L

DELIVERY FORM	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
Pellets	
SPECIAL CHARACTERISTICS	
Bio-Based	
REGIONAL AVAILABILITY	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.