

RILSAN® BESNO P40 TL

PA11-P, EHL, 22-003

Rilsan® BESNO P40 TL resin is a polyamide 11 produced from a renewable source. This natural grade is plasticized and designed for extrusion.

The percentage of renewable carbon according to ASTM D 6866 is **89%**.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Tensile Modulus	- / 345 - / 50000	MPa psi	ISO 527-1/-2
Yield Stress	- / 26 - / 3770	MPa psi	ISO 527-1/-2
Yield Strain	- / 50	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness, after 15 s	60 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 7 - / 3.33	kJ/m² ftlb/in²	ISO 179/1eA
Puncture - Maximum Force, -30°C	- / 6000	N	ISO 6603-2
Puncture Energy, -30°C	- / 70	J	ISO 6603-2
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	181 / *	°C	ISO 11357-1/-3
Temp. of Deflection Under Load, 1.80 MPa	45 / *	°C	ISO 75-1/-2
	113 / *	°F	
Temp. of Deflection Under Load, 0.45 MPa	130 / *	°C	ISO 75-1/-2
	266 / *	°F	
Vicat Softening Temperature, 50°C/h 50N	140 / *	°C	ISO 306
	284 / *	°F	
Coeff. of Linear Thermal Expansion, parallel	110 / *	E-6/K	ISO 11359-1/-2
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	9 / -	-	IEC 60250
Relative Permittivity, 1MHz	4 / -	-	IEC 60250
Dissipation Factor, 100Hz	2440 / -	E-4	IEC 60250
Dissipation Factor, 1MHz	1040 / -	E-4	IEC 60250
Volume Resistivity	- / 1E9	Ohm* m	IEC 62631-3-1

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 12-08-2024

RILSAN® BESNO P40 TL

Surface Resistivity	* / 5E11	Ohm	IEC 62631-3-2
Dielectric (Electric) Strength	- / 23	kV/mm	IEC 60243-1
	- / 584	kV/in	
OTHER PROPERTIES			
%Bio-Based	89	-	ASTM D6866
Water Absorption, 23°C, immersion, equilibrium	1.6 / *	%	ISO 62
Density	1040 / 1040	kg/m³	ISO 1183
	1.04 / 1.04	g/cm³	

MAIN APPLICATIONS:

- Fluid transportation
- Fuel line
- Tubing for use in motor vehicle
- Air brake line

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags, 44 lb bags, 550 kg rigid containers, 1000 lb rigid containers) ready to be processed.


SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.


RILSAN® BESNO P40 TL

DIAGRAMS


VISCOSITY-SHEAR RATE




SHEARSTRESS-SHEAR RATE



DYN. SHEAR MODULUS-TEMPERATURE




STRESS-STRAIN




RILSAN® BESNO P40 TL


SECANT MODULUS-STRAIN




STRESS-STRAIN (ISOCHRONOUS) 73°F



CREEP MODULUS-TIME 73°F




STRESS-STRAIN (ISOCHRONOUS) 212°F




Arkema France - A French "société anonyme", registered in the Nanterre (France)
Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 12-08-2024

RILSAN® BESNO P40 TL

CREEP MODULUS-TIME 212°F



SPECIFIC VOLUME-TEMPERATURE (PVT)



Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 250°C / 280°C.

- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

PROCESSING Profile Extrusion, Other Extrusion	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
DELIVERY FORM Pellets	
ADDITIVES Lubricants, Plasticizer	
SPECIAL CHARACTERISTICS Bio-Based, Heat Stabilized, Light Stabilized	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.