## **PLATAMID®**

# **B 409 PELLETS**

#### Platamid<sup>®</sup> B 409 Pellets

Copolyamide Hot Melt Adhesive / Extrusion Applications

Platamid® B 409 is a high molecular weight, high melting temperature range, partially crystalline copolyamide delivered in pellet form. The special interest of this product is the combination of high melting temperature and high melt viscosity.

Platamid® B 409 can be applied out of a cresolic solution. The thermal activation of the hot melt layer can be accomplished by means of induction of hot air.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	7.2 / *	cm <sup>3</sup> /10 min	ISO 1133
Temperature	200 / *	°C	-
	392 / *	°F	
Load	2.16 / *	kg	-
	4.76 / *	lb	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	178 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1100 / -	kg/m³	ISO 1183
	1.1 / -	g/cm³	

### **AVAILABLE GRADES**

This grade is available:

- dried with lubricant (B 409 TL)
- undried with lubricant (B 409 FL)

#### **PACKAGING**

Platamid® B 409 TL is delivered in 25 kg sealed bags.

Platamid® B 409 FL is delivered in 25 kg sealed bags.

These grades are ready to be processed.

#### SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.



## **PLATAMID®**

# **B 409 PELLETS**

PROCESSING	Headquarters:	
Film Extrusion	Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com  Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com	
DELIVERY FORM		
Pellets		
SPECIAL CHARACTERISTICS		
Adhesive		
REGIONAL AVAILABILITY		
North America, Europe, Asia Pacific, South and Central America, Near East/Africa		

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018 Source: automatically generated TDS from Material Database on 12-08-2024

ARKEMA