

Platamid® H 2513 Powder

Copolyamide Hot Melt Adhesive / Textile Applications

Platamid® H 2513 Powder is a medium melt viscosity copolyamide adhesive powder for the production of fusible interlinings. **Platamid® H 2513 Powder** offers an excellent laundry resistance up to 60°C and an excellent resistance to all kind of steam treatment.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	30 / *	cm ³ /10 min	ISO 1133
Temperature	160 / *	°C	-
	320 / *	°F	-
Load	2.16 / *	kg	-
	4.76 / *	lb	-
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	128 / *	°C	ISO 11357-1/-3

AVAILABLE GRADES

This product is available in different grain sizes:

- Platamid® H 2513 PA 80 (0-80 µm paste dot)
- Platamid® H 2513 PTA 170/20 (0-170 µm powder dot)
- Platamid® H 2513 PTA 170 (80-170 µm double dot)

PACKAGING

- Platamid® H 2513 PA 80 and Platamid® H 2513 PTA 170/20 are delivered in 20 kg sealed bags.
- Platamid® H 2513 PTA 170 is delivered in 20 kg sealed bags and 500 kg sealed big bags (GRVS).

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

PROCESSING	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
Scattering, Paste, Double Dot	
DELIVERY FORM	
Powder	
SPECIAL CHARACTERISTICS	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
Adhesive	
REGIONAL AVAILABILITY	
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.