

# RILSAN® D30 NATURAL

RILSAN® D30 NAT is a polyamide 11 powder obtained from renewable resources with an average diameter of 21 - 27 µm.

RILSAN® D is a range of high performance fine polyamide powders used as multifunctional additives in coatings and varnishes.

The introduction of RILSAN® polyamide powders in formulations is easy thanks to their good dispersion capacity, their reduced impact on rheology and their low density.

RILSAN® polyamide powders are surface modifiers, specifically designed for texture creation.

Abrasion, scratch, impact resistances and flexibility of coatings, inks and varnishes can be significantly improved using RILSAN® polyamide powders.

PROPERTIES	VALUE	UNIT	TEST STANDARD
POWDER PROPERTIES			
Particle Size Distribution, Median Size	21 - 27	mm	-
	0.827 - 1.06	in	
Melting Temperature	186	°C	ISO 1218
	367	°F	
Non Tapped Density	0.34	-	ISO 1068
POWDER COATING PROPERTIES			
Specific Gravity of Coating, 20°C	1.04	-	ISO 1183
Water Absorption, 24h	≤1	%	ISO 62

## APPLICATION PROPERTIES

- **Texturing agent (rough texture)** Texture depends on amount of Orgasol® polyamide powder, dry coating thickness and conditions of curing.
- **Abrasion & Scratch resistance improvement** reinforces the mechanical properties of the coating
- **Compatible with most resins used in coating industry** suitable for solvent-based, water-based and 100% solid UV-curable systems
- **Compliant with FDA regulations (FDA 177-1500 and FDA 175-300)**

## MAIN APPLICATIONS:

- Coil coating
- Wood coating
- Plastic coating

## PACKAGING

This grade is delivered in 15kg bag.

## SHELF LIFE

Five years from the date of delivery. For any use after this limit, please refer to our technical services.

# RILSAN®

## D30 NATURAL

### Headquarters:

Arkema France  
420 rue d'Estienne d'Orves  
92705 Colombes Cedex France  
T +33 (0)1 49 00 80 80  
[hpp.arkema.com](http://hpp.arkema.com)

### Arkema Inc. – High Performance Polymers

900 First Avenue  
King of Prussia, PA 19406  
Tel.: +1 610 205 7000  
[hpp.arkema.com](http://hpp.arkema.com)

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

Arkema France - A French "société anonyme", registered in the Nanterre (France)  
Trade and Companies Register under the number 319 632 790 SDC/11-2018  
Source: automatically generated TDS from Material Database on 20-02-2024