

KYNAR® 340

Kynar® resins are fluorinated thermoplastic homopolymers.

Kynar® 340 resin is a thermoplastic fluorinated polymer resin. The properties are the same as standard grade: chemical resistance, resistance to UV, low permeation, high purity, excellent mechanical behavior. More over, this grade is electrically conductive.

This grade is available as pellet form for injection, extrusion, compression.

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	4	cm ³ /10 min	ISO 1133
Temperature	230	°C	-
	446	°F	-
Load	10	kg	-
	22	lb	-
Melt Flow Rate	3 - 8	g/10min	ASTM D1238
Temperature	230	°C	-
	10	kg	-
Melt Viscosity, 230°C, 100 s ⁻¹	25	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus	1600	MPa	ISO 527-1/-2
	232000	psi	
Yield Stress	40	MPa	ISO 527-1/-2
	5800	psi	
Yield Strain	5	%	ISO 527-1/-2
Nominal Strain at Break	40	%	ISO 527-1/-2
Charpy Notched Impact Strength, +23°C	9	kJ/m ²	ISO 179/1eA
	4.28	ftlb/in ²	
Charpy Notched Impact Strength, -30°C	5	kJ/m ²	ISO 179/1eA
	2.38	ftlb/in ²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	166	°C	ISO 11357-1/-3
Melting Point	165 - 172	°C	ASTM D3418
Oxygen Index	43	%	ISO 4589-1/-2
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	0.07	-	IEC 60250
Volume Resistivity	10000	Ohm* m	IEC 62631-3-1

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

KYNAR® 340

Surface Resistivity	10000	Ohm	IEC 62631-3-2
Dielectric (Electric) Strength	27	kV/mm	IEC 60243-1
	686	kV/in	
OTHER PROPERTIES			
Density	1780	kg/m ³	ISO 1183
	1.78	g/cm ³	
Specific Gravity, 73 °F	1.84 - 1.88	-	ASTM D792

PROCESSING Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion, Transfer Molding	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
DELIVERY FORM Pellets, Granules	
SPECIAL CHARACTERISTICS Conductive	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.