

KYNAR FLEX®

2750-01

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Outstanding characteristics: chemical resistance, imperviousness to UV, barrier properties and high purity.

Kynar Flex® 2750-01 resin is a grade of granules to be used where maximum flexibility or impact strength is required. This product is **NSF/ANSI/CAN 61** certified.

A powder form is available as **Kynar Flex® 2751 resin**.

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	1.9	cm ³ /10 min	ISO 1133
Temperature	230	°C	-
	446	°F	-
Load	5	kg	-
	11	lb	-
Melt Flow Rate	4 - 14	g/10min	ASTM D1238
Temperature	230	°C	-
Load	12.5	kg	-
Melt Viscosity, 230°C, 100 s ⁻¹	20 - 25	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus	526	MPa	ISO 527-1/-2
	76300	psi	
Tensile Modulus, 73 °F	276 - 448	MPa	ASTM D638
	40000 - 65000	psi	
Yield Stress	21	MPa	ISO 527-1/-2
	3050	psi	
Tensile Strength at Yield, 73 °F	13.8 - 21.4	MPa	ASTM D638
	2000 - 3100	psi	
Yield Strain	15	%	ISO 527-1/-2
Elongation at Yield, 73 °F	15 - 25	%	ASTM D638
Nominal Strain at Break	>50	%	ISO 527-1/-2
Tensile Strength at Break, 73 °F	20 - 27.6	MPa	ASTM D638
	2900 - 4000	psi	
Elongation at Break, 73 °F	200 - 400	%	ASTM D638
Taber Abrasion, CS 17 1000g:pad	21 - 25	mg/1000 cycles	ASTM-G195-13A

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

KYNAR FLEX[®]

2750-01

Hardness, Shore D, 73 °F	57 - 62	-	ASTM D2240
Flexural Modulus, 73 °F	276 - 414	MPa	ASTM D790
	40000 - 60000	psi	
Flexural Strength @ 5% Strain, 73 °F	13.8 - 24.1	MPa	ASTM D790
	2000 - 3500	psi	
Compressive Strength, 73 °F	24.1 - 31	MPa	ASTM D695
	3500 - 4500	psi	
Charpy Notched Impact Strength, +23°C	No Break	kJ/m ²	ISO 179/1eA
Notched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
Coefficient of Friction, Static vs. Steel, 73 °F	0.55	-	ASTM D1894
Coefficient of Friction, Dynamic vs. Steel, 73 °F	0.54	-	ASTM D1894
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	134	°C	ISO 11357-1/-3
Melting Point	130 - 138	°C	ASTM D3418
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Glass Transition Temperature (Tg)	-40	°C	ASTM D7028
Temp. of Deflection Under Load, 1.80 MPa	43	°C	ISO 75-1/-2
	109	°F	
Heat Deflection Temperature, 264 Psi, 248 °F/hr	35 - 51.7	°C	ASTM D648
	95 - 125	°F	
Temp. of Deflection Under Load, 0.45 MPa	57	°C	ISO 75-1/-2
	135	°F	
Heat Deflection Temperature, 66 Psi, 248 °F/hr	48.9 - 65.6	°C	ASTM D648
	120 - 150	°F	
Vicat Softening Temperature, 50°C/h 50N	61	°C	ISO 306
	142	°F	
Coeff. of Linear Thermal Expansion, parallel	177	E-6/K	ISO 11359-1/-2
Coefficient of Thermal Expansion, 73 °F	16.2 - 21.6	10E-5/	ASTM D696
	9 - 12	°C 10E-5/	
Burning Behav. at 1.5 mm Nominal Thickness	V-0	°F class	IEC 60695-11-10
	Thickness Tested	1.6	mm
0.0630		in	
Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
	Thickness Tested	0.8	mm
0.0315		in	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

KYNAR FLEX[®]

2750-01

Oxygen Index	49	%	ISO 4589-1/-2
Limiting Oxygen Index	43	%	ASTM D2863
Thermal Conductivity	0.144 - 0.18 1 - 1.25	W/(m K) BTU in	ASTM D433
Specific Heat	745 - 958 0.28 - 0.36	J/(kg K) BTU/(l	DSC
Thermal Decomposition TGA, in air	375 707	°C °F	1% wt. loss
Thermal Decomposition TGA, in nitrogen	410 770	°C °F	1% wt. loss
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	11.5	-	IEC 60250
Relative Permittivity, 1MHz	7	-	IEC 60250
Dielectric Constant, 1 kHz	3.8 - 12.1	-	ASTM D150
Dissipation Factor, 100Hz	240	E-4	IEC 60250
Dissipation Factor, 100 kHz	0.02 - 0.24	-	ASTM D150
Volume Resistivity	2E12	Ohm* m	IEC 62631-3-1
Volume Resistivity, DC 68 °F, 65% R.H.	2E14	Ohm*c m	ASTM D257
Surface Resistivity, 73 °F	4.8E11 - 5.1E11	Ohm per square	ASTM D257
Dielectric (Electric) Strength, 73°F	1.1 - 1.3	kV/mil	ASTM D149
OTHER PROPERTIES			
Water Absorption, 23°C, immersion, equilibrium	0.03	%	ISO 62
Water Absorption	0.03 - 0.06	%	ASTM D570
Density	1780 1.78	kg/m ³ g/cm ³	ISO 1183
Specific Gravity, 73 °F	1.78 - 1.8	-	ASTM D792
OPTICAL PROPERTIES			
Refractive Index @ sodium D line	1.41	-	ASTM D542

MAIN APPLICATIONS:


- flexible tubing
- corrosion protection in the chemical industry
- off-shore
- wire and cable

KYNAR FLEX[®]


2750-01

DIAGRAMS


VISCOSITY-SHEAR RATE




SHEARSTRESS-SHEAR RATE



DYN. SHEAR MODULUS-TEMPERATURE




STRESS-STRAIN




KYNAR FLEX®

2750-01

SECANT MODULUS-STRAIN



SPECIFIC VOLUME-TEMPERATURE (PVT)



<p>PROCESSING</p> <p>Injection Molding, Sheet Extrusion, Other Extrusion, Transfer Molding</p>	<p>Headquarters:</p> <p>Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com</p>
<p>DELIVERY FORM</p> <p>Pellets</p>	
<p>SPECIAL CHARACTERISTICS</p> <p>Heat Stabilized, Light Stabilized</p>	<p>Arkema Inc. – High Performance Polymers</p> <p>900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com</p>
<p>REGIONAL AVAILABILITY</p> <p>North America, Europe, Asia Pacific, South and Central America, Near East/Africa</p>	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.