

KYNAR FLEX®

2850-07

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties.

Kynar Flex® 2850-07 resin is a moderate viscosity version of Kynar Flex® 2850-00 resin in for ease of extrusion and co-extrusion.

It has a UL RTI temperature rating of 140 degrees C.

[UL Yellow Card](#)

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Flow Rate	9 - 16	g/10min	ASTM D1238
Temperature	230	°C	-
Load	12.5	kg	-
Melt Viscosity, 230°C, 100 s ⁻¹	16 - 20	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus	1300 189000	MPa psi	ISO 527-1/-2
Tensile Modulus, 73 °F	1030 - 1520 150000 - 220000	MPa psi	ASTM D638
Yield Stress	40 5800	MPa psi	ISO 527-1/-2
Tensile Strength at Yield, 73 °F	31 - 41.4 4500 - 6000	MPa psi	ASTM D638
Yield Strain	11	%	ISO 527-1/-2
Elongation at Yield, 73 °F	5 - 15	%	ASTM D638
Nominal Strain at Break	>50	%	ISO 527-1/-2
Tensile Strength at Break, 73 °F	27.6 - 48.3 4000 - 7000	MPa psi	ASTM D638
Elongation at Break, 73 °F	30 - 200	%	ASTM D638
Taber Abrasion, CS 17 1000g:pad	6 - 9	mg/1000 cycles	ASTM-G195-13A
Hardness, Shore D, 73 °F	70 - 75	-	ASTM D2240
Flexural Modulus, 73 °F	1030 - 1240 150000 - 180000	MPa psi	ASTM D790

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX[®]

2850-07

Flexural Strength @ 5% Strain, 73 °F	20.7 - 34.5	MPa	ASTM D790
	3000 - 5000	psi	
Compressive Strength, 73 °F	41.4 - 58.6	MPa	ASTM D695
	6000 - 8500	psi	
Charpy Notched Impact Strength, +23°C	No Break	kJ/m ²	ISO 179/1eA
Unnotched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
Notched Impact Strength, 73 °F	0.16 - 0.427	kJ/m	ASTM D256
	3 - 8	ftlb/in	
Coefficient of Friction, Static vs. Steel, 73 °F	0.26	-	ASTM D1894
Coefficient of Friction, Dynamic vs. Steel, 73 °F	0.19	-	ASTM D1894
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	157	°C	ISO 11357-1/-3
Melting Point	155 - 160	°C	ASTM D3418
Glass Transition Temperature (Tg)	-40.6 - -38.3	°C	ASTM D7028
	-41 - -37	°F	
Temperature Rating	140	°C	UL RTI
	284	°F	
Heat Deflection Temperature, 264 Psi, 248 °F/hr	37.8 - 55	°C	ASTM D648
	100 - 131	°F	
Heat Deflection Temperature, 66 Psi, 248 °F/hr	60 - 75	°C	ASTM D648
	140 - 167	°F	
Coefficient of Thermal Expansion, 73 °F	12.6 - 18.5	10E-5/°C	ASTM D696
	7 - 10.3	10E-5/°F	
Burning Behav. at 1.5 mm Nominal Thickness	V-0	class	IEC 60695-11-10
Thickness Tested	1.5	mm	-
	0.0591	in	
Yellow Card available	yes	-	-
Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
Thickness Tested	0.8	mm	-
	0.0315	in	
Limiting Oxygen Index	43	%	ASTM D2863
Thermal Conductivity	0.144 - 0.18	W/(m·K)	ASTM D433
	1 - 1.25	BTU in/(hr ft ² °F)	
Specific Heat	745 - 958	J/(kg·°C)	DSC
	0.28 - 0.36	BTU/(lb·°F)	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX[®]

2850-07

Thermal Decomposition TGA, in air	375	°C	1% wt. loss
	707	°F	
Thermal Decomposition TGA, in nitrogen	410	°C	1% wt. loss
	770	°F	
Relative Thermal Index, Mechanical	140	°C	UL 746B
	284	°F	
Relative Thermal Index, Electrical	140	°C	UL 746B
	284	°F	
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	6.85	-	IEC 60250
Dielectric Constant, 1 kHz	3.5 - 10.2	-	ASTM D150
Dissipation Factor, 100Hz	0.12	E-4	IEC 60250
Dissipation Factor, 100 kHz	0.01 - 0.22	-	ASTM D150
Volume Resistivity	2E12	Ohm* m	IEC 62631-3-1
Volume Resistivity, DC 68 °F, 65% R.H.	2E14	Ohm*c m	ASTM D257
Dielectric (Electric) Strength	1.4	kV/mm	IEC 60243-1
	35.6	kV/in	
Dielectric (Electric) Strength, 73°F	1.3 - 1.6	kV/mil	ASTM D149
OTHER PROPERTIES			
Water Absorption, 23°C, immersion, equilibrium	0.03	%	ISO 62
Density	1770	kg/m³	ISO 1183
	1.77	g/cm³	
Specific Gravity, 73 °F	1.77 - 1.8	-	ASTM D792
OPTICAL PROPERTIES			
Refractive Index @ sodium D line	1.42	-	ASTM D542

MAIN APPLICATIONS:

- injection molded applications requiring the high chemical and temperature resistance properties of Kynar 2850-00 resin

KYNAR FLEX[®]

2850-07

REGIONAL AVAILABILITY	Headquarters:
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.