

KYNAR FLEX®

3030-50

Kynar Flex® 3030-50 resin is a copolymer of vinylidene fluoride and hexafluoropropylene specifically designed for cable, tubing and heat shrink tubing applications.

Characteristics:

- Excellent crosslink efficiency
- Very high flexibility
- High melting point
- Excellent low temperature impact resistance

A powder form is also available: **Kynar Flex® 3031-50**.

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Flow Rate	2.5 - 7.5	g/10min	ASTM D1238
Temperature	230	°C	-
Load	12.5	kg	-
Melt Viscosity, 230°C, 100 s ⁻¹	21 - 30	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus, 73 °F	207 - 345 30000 - 50000	MPa psi	ASTM D638
Tensile Strength at Yield, 73 °F	11.7 - 15.9 1700 - 2300	MPa psi	ASTM D638
Elongation at Yield, 73 °F	25 - 40	%	ASTM D638
Tensile Strength at Break, 73 °F	18.6 - 24.1 2700 - 3500	MPa psi	ASTM D638
Elongation at Break, 73 °F	≥500	%	ASTM D638
Taber Abrasion, CS 17 1000g:pad	28 - 33	mg/1000 cycles	ASTM-G195-13A
Hardness, Shore D, 73 °F	50 - 60	-	ASTM D2240
Flexural Modulus, 73 °F	248 - 303 36000 - 44000	MPa psi	ASTM D790
Notched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
THERMAL PROPERTIES			
Melting Point	160 - 168	°C	ASTM D3418
Glass Transition Temperature (Tg)	-40	°C	ASTM D7028
Temperature Rating	150 302	°C °F	UL RTI

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

KYNAR FLEX[®]

3030-50

Coefficient of Thermal Expansion, 73 °F	15.3 - 19.4	10E-5/	ASTM D696
	8.5 - 10.8	°C 10E-5/	
Limiting Oxygen Index	≥43	%	ASTM D2863
ELECTRICAL PROPERTIES			
Volume Resistivity, DC 68 °F, 65% R.H.	7.8E13 - 8E13	Ohm*c m	ASTM D257
Surface Resistivity, 73 °F	7.6E11 - 7.9E11	Ohm per square	ASTM D257
Dielectric (Electric) Strength, 73°F	1 - 1.2	kV/mil	ASTM D149
OTHER PROPERTIES			
Water Absorption	≤0.05	%	ASTM D570
Specific Gravity, 73 °F	1.78 - 1.82	-	ASTM D792

PROCESSING	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
Profile Extrusion, Other Extrusion	
DELIVERY FORM	
Pellets	
REGIONAL AVAILABILITY	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.