



Orgalloy® EM 067 HSP resin is a flexible polyamide designed to be used for refrigerant barrier layer in air conditioning rubber hose.

Packaging:

This grade is delivered dried in sealed packaging (20kg bags) ready to be processed.

Shelf life:

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	1 / *	cm ³ /10 min	ISO 1133
Temperature	235 / *	°C	-
	455 / *	°F	
Load	5 / *	kg	-
	11 / *	lb	
MECHANICAL PROPERTIES			
Tensile Modulus	- / 572	MPa	ISO 527-1/-2
	- / 83000	psi	
Stress at 50% Strain	- / 32	MPa	ISO 527-1/-2
	- / 4640	psi	
Strain at Break	- / >50	%	ISO 527-1/-2
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	215 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1140 / 1140	kg/m³	ISO 1183
	1.14 / 1.14	g/cm³	

Processing conditions:

- Drying time (only necessary for bags opened for more than two hours): 4-16 hours at 80-90°C
- Extrusion melt temperature (min-recommended-max): 240-260-300°C





PROCESSING	Headquarters:	
Film Extrusion, Profile Extrusion, Other Extrusion	Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers	
DELIVERY FORM		
Pellets		
ADDITIVES		
Plasticizer	900 First Avenue	
REGIONAL AVAILABILITY	King of Prussia, PA 19406 Tel.: +1 610 205 7000	
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	hpp.arkema.com	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

