

# PEBAX<sup>®</sup>

## 3533 SA 01 MED

Polyether block amide **Pebax<sup>®</sup> 3533 SA 01 MED resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide.

This grade offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices.

Upon request, letters regarding USP Class VI compliance can be provided.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
<b>RHEOLOGICAL PROPERTIES</b>			
Molding Shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	1.2 / *	%	ISO 294-4, 2577
<b>MECHANICAL PROPERTIES</b>			
Tensile Modulus	19 / 18	MPa	ISO 527-1/-2
	2760 / 2610	psi	
Stress at 50% Strain	4 / 4	MPa	ISO 527-1/-2
	580 / 580	psi	
Strain at Break	>50 / >50	%	ISO 527-1/-2
Strain at Break TPE	>300 / *	%	ISO 527-1/-2
Stress at Break TPE	39 / *	MPa	ISO 527-1/-2
	5660 / *	psi	
Shore A Hardness, after 15 s	80 / *	-	ISO 868
Shore D Hardness, after 15 s	25 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / No Break	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL PROPERTIES</b>			
Melting Temperature, 10°C/min	144 / *	°C	ISO 11357-1/-3
<b>OTHER PROPERTIES</b>			
Water Absorption, 23°C, immersion, equilibrium	1.2 / *	%	ISO 62
Humidity Absorption, 23°C, RH50%, equilibrium	0.4 / *	%	ISO 62
Density	1000 / 1000	kg/m <sup>3</sup>	ISO 1183
	1 / 1	g/cm <sup>3</sup>	

**MAIN APPLICATIONS:** • Catheters

• Flexible injected parts

### PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018  
Source: automatically generated TDS from Material Database on 12-08-2024

# PEBAX<sup>®</sup>

## 3533 SA 01 MED

### SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

### Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 180°C / 210°C / 240°C.
- Typical mold temperature : 10 – 30°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 55-65°C.

### Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 190°C / 205°C / 220°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 55-65°C.

<b>PROCESSING</b> Injection Molding, Film Extrusion, Other Extrusion	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
<b>DELIVERY FORM</b> Pellets	
<b>ADDITIVES</b> Lubricants	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
<b>SPECIAL CHARACTERISTICS</b> Heat Stabilized	
<b>REGIONAL AVAILABILITY</b> North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.