

# RILSAN® BESNO TL

PA11,EHL,22-010

Rilsan® BESNO TL resin is a polyamide 11 produced from a renewable source. This natural grade is designed for extrusion.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
<b>RHEOLOGICAL PROPERTIES</b>			
Melt Volume-Flow Rate	1 / *	cm <sup>3</sup> /10 min	ISO 1133
Temperature	235 / *	°C	-
	455 / *	°F	-
Load	2.16 / *	kg	-
	4.76 / *	lb	-
<b>MECHANICAL PROPERTIES</b>			
Tensile Modulus	- / 1280	MPa	ISO 527-1/-2
	- / 186000	psi	
Yield Stress	- / 38	MPa	ISO 527-1/-2
	- / 5510	psi	
Yield Strain	- / 5	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness, after 15 s	72 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / 11	kJ/m <sup>2</sup>	ISO 179/1eA
	- / 5.23	ftlb/in <sup>2</sup>	
Charpy Notched Impact Strength, -30°C	- / 12	kJ/m <sup>2</sup>	ISO 179/1eA
	- / 5.71	ftlb/in <sup>2</sup>	
Puncture - Maximum Force, -30°C	- / 6000	N	ISO 6603-2
Puncture Energy, -30°C	- / 70	J	ISO 6603-2
<b>THERMAL PROPERTIES</b>			
Melting Temperature, 10°C/min	186 / *	°C	ISO 11357-1/-3
Temp. of Deflection Under Load, 1.80 MPa	50 / *	°C	ISO 75-1/-2
	122 / *	°F	
Temp. of Deflection Under Load, 0.45 MPa	145 / *	°C	ISO 75-1/-2
	293 / *	°F	
Vicat Softening Temperature, 50°C/h 50N	160 / *	°C	ISO 306
	320 / *	°F	
Coeff. of Linear Thermal Expansion, parallel	85 / *	E-6/K	ISO 11359-1/-2

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018  
 Source: automatically generated TDS from Material Database on 12-08-2024

# RILSAN® BESNO TL

Burning Behav. at 1.5 mm Nominal Thickness	HB / *	class	IEC 60695-11-10
Thickness Tested	1.6 / *	mm	-
	0.0630 / *	in	
Yellow Card available	yes / *	-	-
<b>ELECTRICAL PROPERTIES</b>			
Relative Permittivity, 100Hz	3 / -	-	IEC 60250
Relative Permittivity, 1MHz	3 / -	-	IEC 60250
Dissipation Factor, 100Hz	308 / -	E-4	IEC 60250
Dissipation Factor, 1MHz	183 / -	E-4	IEC 60250
Volume Resistivity	- / 1E12	Ohm* m	IEC 62631-3-1
Surface Resistivity	* / 1E14	Ohm	IEC 62631-3-2
Dielectric (Electric) Strength	- / 30	kV/mm	IEC 60243-1
	- / 762	kV/in	
<b>OTHER PROPERTIES</b>			
Water Absorption, 23°C, immersion, equilibrium	1.9 / *	%	ISO 62
Density	1020 / 1020	kg/m <sup>3</sup>	ISO 1183
	1.02 / 1.02	g/cm <sup>3</sup>	

## MAIN APPLICATIONS:

- Fluid transportation

## PACKAGING:


This grade is delivered dried in sealed packaging (25 kg bags, 44 lb bags, 1000 lb rigid containers) ready to be processed.

## SHELF LIFE:


Two years from the delivery. For any use above this limit, please refer to our technical services.

## DIAGRAMS


### VISCOSITY-SHEAR RATE




### SHEARSTRESS-SHEAR RATE




### DYN. SHEAR MODULUS-TEMPERATURE




### STRESS-STRAIN




## SECANT MODULUS-STRAIN




## STRESS-STRAIN (ISOCHRONOUS) 73°F



## CREEP MODULUS-TIME 73°F




## STRESS-STRAIN (ISOCHRONOUS) 176°F



# RILSAN® BESNO TL

## CREEP MODULUS-TIME 176°F



### Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 250°C / 280°C.

- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

<p><b>PROCESSING</b></p> <p>Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion</p>	<p>Headquarters:</p> <p>Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com</p> <p>Arkema Inc. – High Performance Polymers</p> <p>900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com</p>
<p><b>DELIVERY FORM</b></p> <p>Pellets</p>	
<p><b>ADDITIVES</b></p> <p>Lubricants</p>	
<p><b>SPECIAL CHARACTERISTICS</b></p> <p>Bio-Based, Heat Stabilized, Light Stabilized</p>	
<p><b>REGIONAL AVAILABILITY</b></p> <p>North America, Europe, Asia Pacific, South and Central America, Near East/Africa</p>	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.