

KYNAR FLEX®

3030-50

Kynar Flex® 3030-50 resin is a copolymer of vinylidene fluoride and hexafluoropropylene specifically designed for cable, tubing and heat shrink tubing applications.

Characteristics:

- Excellent crosslink efficiency
- Very high flexibility
- High melting point
- Excellent low temperature impact resistance

A powder form is also available: Kynar Flex® 3031-50.

特性	値	単位	テスト基準
レオロジー特性			
メルトフローレイト	2.5 - 7.5	g/10m in	ASTM D1238
温度	230	°C	-
荷重	12.5	kg	-
熔融粘度, 230°C, 100 s ⁻¹	21 - 30	kPoise	ASTM D3835
機械的特性			
引張弾性率, 73 °F	207 - 345	MPa	ASTM D638
	30000 - 50000	psi	
降伏応力, 73 °F	11.7 - 15.9	MPa	ASTM D638
	1700 - 2300	psi	
降伏点伸び, 73 °F	25 - 40	%	ASTM D638
破壊応力, 73 °F	18.6 - 24.1	MPa	ASTM D638
	2700 - 3500	psi	
破断伸び, 73 °F	≥ 500	%	ASTM D638
Taber 耐摩耗性, CS 17 1000g:pad	28 - 33	mg/10 00 cycles	ASTM-G195-13A
ショア硬さ, D, 73 °F	50 - 60	-	ASTM D2240
曲げ弾性率, 73 °F	248 - 303	MPa	ASTM D790
	36000 - 44000	psi	
ノッチ付き衝撃強さ, 73 °F	未破壊	kJ/m	ASTM D256
熱的特性			
熔融温度	160 - 168	°C	ASTM D3418
ガラス転移温度 (Tg)	-40	°C	ASTM D7028
温度定格	150	°C	UL RTI
	302	°F	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX[®]

3030-50

線膨張係数, 73 °F	15.3 - 19.4	10E-5/ °C	ASTM D696
	8.5 - 10.8	10E-5/ °F	
酸素指数	≥ 43	%	ASTM D2863
電気的特性.			
体積抵抗率, DC 68 °F, 65% R.H.	7.8E13 - 8E13	Ohm* cm	ASTM D257
表面抵抗率, 73 °F	7.6E11 - 7.9E11	Ohm per square	ASTM D257
耐電圧, 73°F	1 - 1.2	kV/mil	ASTM D149
その他の特性.			
吸水率	≤ 0.05	%	ASTM D570
比重, 73 °F	1.78 - 1.82	-	ASTM D792

成形加工法 異形押出成形, その他の押出成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 ペレット	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.