

# KYNAR FLEX®

## PPA 2200

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® PPA 2200 resin is specially designed pellet used as a polymer process aid (PPA) for polyolefins.

The use of Kynar Flex® PPA 2200 resin at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

特性	値	単位	テスト基準
熱的特性			
溶融温度, 10°C/min	144	°C	ISO 11357-1/-3
その他の特性			
密度	700	kg/m³	ISO 1183
	0.7	g/cm³	
かさ密度	0.6 - 0.8	g/cm³	1% wt. loss

成形加工法	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
フィルム押出成形, シート押出成形, その他の押出成形	
納入形状	
顆粒.	
領域別の利用可能性	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.