

KYNAR SUPERFLEX[®]

2500-20

Kynar Superflex[®] resin is a thermoplastic fluorinated polymer.

The properties are the same as standard grades: chemical resistance, resistance to UV, low permeation, high purity, excellent mechanical behavior.

More over, this grade is very flexible and is suitable in electrical isolation cable, tubing and co-extrusion.

This grade is available as pellet form for injection, extrusion, compression.

特性	値	単位	テスト基準
レオロジー特性			
メルトポリュームレイト	5.8	cm ³ /10min	ISO 1133
温度	232	°C	-
	450	°F	-
荷重	3.8	kg	-
	8.38	lb	-
メルトフローレイト	1 - 15	g/10min	ASTM D1238
温度	230	°C	-
荷重	3.8	kg	-
溶融粘度, 230°C, 100 s ⁻¹	9 - 16	kPoise	ASTM D3835
機械的特性			
引張弾性率	350	MPa	ISO 527-1/-2
	50800	psi	
引張弾性率, 73 °F	241 - 379	MPa	ASTM D638
	35000 - 55000	psi	
降伏応力	15	MPa	ISO 527-1/-2
	2180	psi	
降伏応力, 73 °F	11.7 - 19.3	MPa	ASTM D638
	1700 - 2800	psi	
降伏ひずみ	18	%	ISO 527-1/-2
降伏点伸び, 73 °F	17 - 25	%	ASTM D638
破壊呼びひずみ	>50	%	ISO 527-1/-2
破壊応力, 73 °F	13.8 - 31	MPa	ASTM D638
	2000 - 4500	psi	
破断伸び, 73 °F	300 - 400	%	ASTM D638
Taber 耐摩耗性, CS 17 1000g:pad	28 - 33	mg/100 cycles	ASTM-G195-13A

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR SUPERFLEX[®]

2500-20

シヨア硬さ, D, 73 °F	50 - 57	-	ASTM D2240
曲げ弾性率, 73 °F	193 - 276	MPa	ASTM D790
	28000 - 40000	psi	
5%伸び時の曲げ強度, 73 °F	10.3 - 17.2	MPa	ASTM D790
	1500 - 2500	psi	
圧縮強度, 73 °F	13.8 - 20.7	MPa	ASTM D695
	2000 - 3000	psi	
ノッチ付きシャルピー衝撃強さ, +23°C	未破壊	kJ/m ²	ISO 179/1eA
衝撃試験, 73 °F	未破壊	kJ/m	ASTM D256
ノッチ付き衝撃強さ, 73 °F	未破壊	kJ/m	ASTM D256
摩擦係数, 静力学対鋼, 73°F	0.49	-	ASTM D1894
摩擦係数, 動的対鋼, 73°F	0.54	-	ASTM D1894
熱的特性			
溶融温度, 10°C/min	122	°C	ISO 11357-1/-3
溶融温度	117 - 125	°C	ASTM D3418
ガラス転移点, 10°C/min	-40	°C	ISO 11357-1/-2
ガラス転移温度 (Tg)	-43.3 - -40	°C	ASTM D7028
	-46 - -40	°F	
荷重たわみ温度, 1.80 MPa	31	°C	ISO 75-1/-2
	88	°F	
荷重たわみ温度, 264 Psi, 248 °F/hr	26.7 - 37.8	°C	ASTM D648
	80 - 100	°F	
線膨張係数, 73 °F	15.3 - 19.4	10E-5/ °C	ASTM D696
	8.5 - 10.8	10E-5/ °F	
1.5mm厚さでの燃焼性	V-0	class	IEC 60695-11-10
試験片の厚さ	1.5	mm	-
	0.0591	in	
Yellow Card 可用	はい	-	-
厚さhでの燃焼性	V-0	class	IEC 60695-11-10
試験片の厚さ	1.0	mm	-
	0.0394	in	
酸素指数	44	%	ISO 4589-1/-2
酸素指数	42	%	ASTM D2863
熱伝導率	0.144 - 0.18	W/(m K)	ASTM D433
	1 - 1.25	BTU in /(hr ft ² F)	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR SUPERFLEX[®]

2500-20

比熱	745 - 958	J/(kg K)	DSC
	0.28 - 0.36	BTU/(l	
空気中の熱分解	375	°C	1% wt. loss
	707	°F	
窒素中での熱分解	410	°C	1% wt. loss
	770	°F	
電気的特性.			
比誘電率, 1 kHz	4.5 - 13.5	-	ASTM D150
誘電正接, 100 kHz	0.05 - 0.29	-	ASTM D150
体積抵抗率, DC 68 °F, 65% R.H.	2E14	Ohm* cm	ASTM D257
表面抵抗率, 73 °F	8.5E11 - 9.2E11	Ohm per square	ASTM D257
耐電圧	12	kV/m	IEC 60243-1
	305	kV/in	
耐電圧, 73°F	0.8 - 1.1	kV/mil	ASTM D149
その他の特性.			
吸水率, 23°C, immersion, equilibrium	0.03	%	ISO 62
吸水率	≤ 0.07	%	ASTM D570
密度	1790	kg/m ³	ISO 1183
	1.79	g/cm ³	
比重, 73 °F	1.8 - 1.82	-	ASTM D792
光学特性			
Refractive Index @ sodium D line	1.4	-	ASTM D542

成形加工法	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
射出成形, シート押出成形, コーティング, トランスファー成形	
納入形状	
ペレット	
特殊な特性	
熱安定化, 光安定化	
領域別の利用可能性	
北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

Arkema France - A French "société anonyme", registered in the Nanterre (France)
 Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR SUPERFLEX[®]

2500-20

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

Arkema France - A French "société anonyme", registered in the Nanterre (France)
Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024