

# ORGALLOY®

## LT 4060 ES BLACK T6L

Orgalloy® LT 4060 ES BLACK T6L resin is a polyamide alloy especially designed for extrusion blow molding. This black grade offers an excellent thermal resistance, cold impact performance and flexibility.

特性	乾燥/調湿	単位	テスト基準
レオロジー特性			
メルトボリュームレイト	0.5 / *	cm³/10min	ISO 1133
温度	235 / *	°C	-
	455 / *	°F	-
荷重	5 / *	kg	-
	11 / *	lb	-
機械的特性			
引張弾性率	570 / 230	MPa	ISO 527-1/-2
	82700 / 33400	psi	
50%ひずみ時応力	22 / 16	MPa	ISO 527-1/-2
	3190 / 2320	psi	
破壊ひずみ	>50 / >50	%	ISO 527-1/-2
ショア硬さD, 15 s	50 / *	-	ISO 868
シャルピー衝撃強さ, +23°C	未破壊 / 未破壊	kJ/m²	ISO 179/1eU
ノッチ付きシャルピー衝撃強さ, +23°C	79 / 78	kJ/m²	ISO 179/1eA
	37.6 / 37.1	ftlb/in²	
熱的特性			
熔融温度, 10°C/min	220 / *	°C	ISO 11357-1/-3
荷重たわみ温度, 0.45 MPa	60 / *	°C	ISO 75-1/-2
	140 / *	°F	
ビカット軟化温度, 50°C/h 50N	62 / *	°C	ISO 306
	144 / *	°F	
1.5mm厚さでの燃焼性	HB / *	class	IEC 60695-11-10
試験片の厚さ	1.6 / *	mm	-
	0.0630 / *	in	
厚さhでの燃焼性	HB / *	class	IEC 60695-11-10
試験片の厚さ	3.2 / *	mm	-
	0.1260 / *	in	
電気的特性.			
耐トラッキング性	* / 600	-	IEC 60112
その他の特性.			
吸水率, 23°C, immersion, equilibrium	5 / *	%	ISO 62

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018  
Source: automatically generated TDS from Material Database on 20-02-2024

# ORGALLOY®

## LT 4060 ES BLACK T6L

吸湿率	1.1 / *	%	ISO 62
密度	1040 / 1040	kg/m <sup>3</sup>	ISO 1183
	1.04 / 1.04	g/cm <sup>3</sup>	

### Main applications:

- Automotive air intake ducts (clean air duct and outside intercooler tube)

### Packaging:


This grade is delivered dried in sealed packaging (25kg bags) ready to be processed.

### Shelf life:

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

## 機能

### PVT



### Processing conditions:

- Drying time (only necessary for bags opened for more than two hours): 4-8 hours at 80°C
- Extrusion melt temperature (min-recommended-max): 250-260-270°C

# ORGALLOY®

## LT 4060 ES BLACK T6L

成形加工法 ブロー成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com  Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 ペレット	
特殊な特性 熱安定化, 光安定化	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.