

PEBAX[®]

MH 1657

Polyether block amide Pebax[®] MH 1657 resin is a thermoplastic elastomer made of flexible polyether and rigid polyamide. Pebax[®] MH 1657 resin is an inherently dissipative polymer and can be dry blended or compounded with an isolative polymer to lower the surface resistivity of the final part.

This hydrophilic grade when extruded into either a thin film or laminated on to a substrate also offers excellent permeability to moisture vapor while remaining waterproof.

特性	乾燥/調湿	単位	テスト基準
機械的特性			
引張弾性率	90 / 80	MPa	ISO 527-1/-2
	13100 / 11600	psi	
50%ひずみ時応力	13 / 12	MPa	ISO 527-1/-2
	1890 / 1740	psi	
破壊ひずみ	>50 / >50	%	ISO 527-1/-2
ショア硬さD, 15 s	40 / *	-	ISO 868
シャルピー衝撃強さ, +23°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eU
シャルピー衝撃強さ, -30°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eU
ノッチ付きシャルピー衝撃強さ, +23°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eA
熱的特性			
溶融温度, 10°C/min	204 / *	°C	ISO 11357-1/-3
ガラス転移点, 10°C/min	-40 / *	°C	ISO 11357-1/-2
電気的特性			
体積抵抗率	- / 2E7	Ohm* m	IEC 62631-3-1
表面抵抗率	* / 1.5E9	Ohm	IEC 62631-3-2
その他の特性			
吸水率, 23°C, immersion, equilibrium	120 / *	%	ISO 62
吸湿率	4.5 / *	%	ISO 62
密度	1140 / -	kg/m ³	ISO 1183
	1.14 / -	g/cm ³	

Main applications:

- Breathable membranes
- Permanent antistatic additive

Packaging:

This grade is delivered dried in sealed packaging (25 kg bags and 550 kg rigid containers) ready to be processed.

Shelf Life:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Injection molding process conditions:

- Typical melt temperature (Min / Recommended / Max): 230°C / 240°C / 260°C.
- Typical mold temperature: 25–60°C.
- Drying time and temperature (only necessary for bags/containers opened for more than two hours): 5-7 hours at 70-90°C.

PEBAX[®]

MH 1657

Extrusion process conditions:

- Typical melt temperature (Min / Recommended / Max): 230°C / 250°C / 280°C.

- Drying time and temperature (only necessary for bags/containers opened for more than two hours): 5-7 hours at 70-90°C.

成形加工法 射出成形, フィルム押出成形, 異形押出成形, その他の押出成形, トランスファー成形, 注型, 熱成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
納入形状 ペレット	
特殊な特性 帯電防止, 熱安定化	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.