

# PEBAX® RNEW® 30R51 SA 01

Polyether block Pebax® Rnew® 30R51 SA 01 resin is a thermoplastic elastomer made of flexible polyether and rigid polyamide based on renewable resources.

Pebax® Rnew® 30R51 SA 01 resin is an inherently antistatic polymer and can be dry blended or compounded with a polymer matrix to lower the surface resistivity of the final part. This grade is particularly recommended for PMMA matrices. This hydrophilic grade when extruded into either a thin film or laminated on to a substrate offers excellent permeability to moisture vapor while remaining waterproof.

The percentage of renewable carbon measured according to ASTM D6866 is 47 %.

Refractive index according to an internal method is 1.49.

特性	乾燥/調湿	単位	テスト基準
機械的特性			
引張弾性率	- / 59	MPa	ISO 527-1/-2
	- / 8560	psi	
50%ひずみ時応力	- / 7	MPa	ISO 527-1/-2
	- / 1020	psi	
破壊ひずみ	- / >50	%	ISO 527-1/-2
破壊ひずみ TPE	>300 / *	%	ISO 527-1/-2
破壊応力 TPE	16 / *	MPa	ISO 527-1/-2
	2320 / *	psi	
ショア硬さD, 15 s	30 / *	-	ISO 868
熱的特性			
熔融温度, 10°C/min	150 / *	°C	ISO 11357-1/-3
電気的特性			
体積抵抗率	1E8 / 1E8	Ohm* m	IEC 62631-3-1
表面抵抗率	* / 1E9	Ohm	IEC 62631-3-2
その他の特性			
%Bio-Based	47	-	ASTM D6866
吸水率, 23°C, immersion, equilibrium	72 / *	%	ISO 62
吸湿率	2.5 / *	%	ISO 62
密度	1010 / -	kg/m³	ISO 1183
	1.01 / -	g/cm³	

Main applications:

- Permanent antistatic additive for PMMA matrices
- Breathable membranes
- Note: this grade is not recommended by Arkema for usage in medical applications

Packaging:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018  
Source: automatically generated TDS from Material Database on 20-02-2024

# PEBAX<sup>®</sup> RNEW<sup>®</sup> 30R51 SA 01

## Shelf Life:

Two years from the delivery. For any use above this limit, please refer to our technical services.

## Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 200°C / 240°C / 270°C.
- Typical mold temperature: 25–60°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-6 hours at 65-75°C.

## Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 210°C / 220°C / 230°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-6 hours at 65-75°C.

成形加工法 射出成形, その他の押出成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com  Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 ペレット	
特殊な特性 帯電防止, バイオベース, 熱安定化	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.