

PEBAX[®] RNEW[®] 40R53 SP 01

Polyether block Pebax® Rnew® 40R53 SP 01 resin is a thermoplastic elastomer made of flexible polyether and rigid polyamide based on renewable resources. This SP grade has been developed to be heat and UV resistant.

The percentage of renewable carbon measured according to ASTM D6866 is 45 %.

特性	乾燥/調湿	単位	テスト基準
レオロジー特性			
成形収縮率, 平行	0.6 / *	%	ISO 294-4, 2577
成形収縮率, 直角	0.7 / *	%	ISO 294-4, 2577
機械的特性			
引張弾性率	- / 75	MPa	ISO 527-1/-2
	- / 10900	psi	
50%ひずみ時応力	- / 8.2	MPa	ISO 527-1/-2
	- / 1190	psi	
破壊ひずみ	- / >50	%	ISO 527-1/-2
破壊ひずみ TPE	>300 / *	%	ISO 527-1/-2
破壊応力 TPE	45 / *	MPa	ISO 527-1/-2
	6530 / *	psi	
ショア硬さD, 15 s	39 / *	-	ISO 868
シャルピー衝撃強さ, +23°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eU
シャルピー衝撃強さ, -30°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eU
ノッチ付きシャルピー衝撃強さ, +23°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eA
ノッチ付きシャルピー衝撃強さ, -30°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eA
熱的特性			
溶融温度, 10°C/min	148 / *	°C	ISO 11357-1/-3
その他の特性			
%Bio-Based	45	-	ASTM D6866
吸水率, 23°C, immersion, equilibrium	1.4 / *	%	ISO 62
吸湿率	0.5 / *	%	ISO 62
密度	1030 / 1030	kg/m ³	ISO 1183
	1.03 / 1.03	g/cm ³	

Main applications:

- Flexible injected parts

Packaging:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

Shelf Life:


Two years from the delivery. For any use above this limit, please refer to our technical services.

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024


PEBAX[®] RNEW[®] 40R53 SP 01

機能

応力-ひずみ.



割線弾性率-ひずみ.



Processing conditions (injection molding):

- Typical melt temperature (Min / Recommended / Max) : 200°C / 240°C / 270°C.
- Typical mold temperature : 10 – 30°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 60-70°C.

Processing conditions (extrusion):

- Typical melt temperature (Min / Recommended / Max): 210°C / 220°C / 230°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-8 hours at 60-70°C.

成形加工法 射出成形, フィルム押出成形, 異形押出成形, その他の押出成形, トランスファー成形, 注型, 熱成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 ペレット	
特殊な特性 バイオベース, 熱安定化, 光安定化	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

Arkema France - A French "société anonyme", registered in the Nanterre (France)
 Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 20-02-2024

PEBAX[®] RNEW[®] 40R53 SP 01

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.