

RILSAMID®

AMN BLACK P20 TLD

PA12-P, MHLR, 12-005

Rilsamid® AMN BLACK P20 TLD resin is a black colored polyamide. This grade is plasticized and designed for injection molding.

特性	乾燥/調湿	単位	テスト基準
レオロジー特性			
メルトボリュームレイト	44 / *	cm³/10min	ISO 1133
温度	235 / *	°C	-
	455 / *	°F	-
荷重	2.16 / *	kg	-
	4.76 / *	lb	-
成形収縮率, 平行	1.9 / *	%	ISO 294-4, 2577
成形収縮率, 直角	1.9 / *	%	ISO 294-4, 2577
機械的特性			
引張弾性率	- / 550	MPa	ISO 527-1/-2
	- / 79800	psi	
降伏応力	- / 31	MPa	ISO 527-1/-2
	- / 4500	psi	
降伏ひずみ	- / 19	%	ISO 527-1/-2
破壊呼びひずみ	- / >50	%	ISO 527-1/-2
シャルピー衝撃強さ, +23°C	- / 未破壊	kJ/m²	ISO 179/1eU
シャルピー衝撃強さ, -30°C	- / 未破壊	kJ/m²	ISO 179/1eU
ノッチ付きシャルピー衝撃強さ, +23°C	- / 18	kJ/m²	ISO 179/1eA
	- / 8.56	ftlb/in²	
ノッチ付きシャルピー衝撃強さ, -30°C	- / 4	kJ/m²	ISO 179/1eA
	- / 1.9	ftlb/in²	
熱的特性			
溶融温度, 10°C/min	174 / *	°C	ISO 11357-1/-3
その他の特性			
密度	1020 / 1020	kg/m³	ISO 1183
	1.02 / 1.02	g/cm³	

Processing conditions, Injection:

- Typical melt temperature (Min / Recommended / Max) : 250°C / 270°C / 290°C.
- Mold temperature : 20 - 40°C
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 80 - 90°C.

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

RILSAMID®

AMN BLACK P20 TLD

成形加工法 射出成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 ペレット	
添加剤 離型剤, 可塑剤	
特殊な特性 熱安定化, 光安定化	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.