

RILSAMID®

ASR 13

ISO 16396 - PA12, CF15, M1GHL, C16-080

Rilsamid® ASR 13 resin is a carbon fiber reinforced polyamide.

This black colored grade is designed for injection moulding.

特性	乾燥/調湿	単位	テスト基準
レオロジー特性			
メルトボリュームレイト	10 / *	cm³/10min	ISO 1133
温度	235 / *	°C	-
	455 / *	°F	-
荷重	5 / *	kg	-
	11 / *	lb	-
メルトフローレイト	≥ 10	g/10min	ASTM D1238
機械的特性			
引張弾性率	9600 / 9000	MPa	ISO 527-1/-2
	1.39E6 / 1.31E6	psi	
破壊応力	127 / 115	MPa	ISO 527-1/-2
	18400 / 16700	psi	
破壊ひずみ	- / 4	%	ISO 527-1/-2
シャルピー衝撃強さ, +23°C	45 / 46	kJ/m²	ISO 179/1eU
	21.4 / 21.9	ftlb/in²	
シャルピー衝撃強さ, -30°C	47 / 48	kJ/m²	ISO 179/1eU
	22.4 / 22.8	ftlb/in²	
ノッチ付きシャルピー衝撃強さ, +23°C	11 / 11	kJ/m²	ISO 179/1eA
	5.23 / 5.23	ftlb/in²	
ノッチ付きシャルピー衝撃強さ, -30°C	8 / 7	kJ/m²	ISO 179/1eA
	3.81 / 3.33	ftlb/in²	
熱的特性			
溶融温度, 10°C/min	178 / *	°C	ISO 11357-1/-3
空気中の熱分解	223	°C	1% wt. loss
	434	°F	
窒素中での熱分解	223	°C	1% wt. loss
	433	°F	
電気的特性.			
表面抵抗率	* / 100000	Ohm	IEC 62631-3-2
その他の特性.			

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

RILSAMID®

ASR 13

吸水率, 23°C, immersion, equilibrium	1.5 / *	%	ISO 62
吸湿率	0.6 / *	%	ISO 62
密度	1080 / -	kg/m ³	ISO 1183
	1.08 / -	g/cm ³	

Packaging :

This grade is delivered dried in sealed packaging (25 kg bags / 450 kg rigid containers) ready to be processed

Shelf life :

Two years from the delivery.

For any use above this limit please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 240°C / 260°C / 280°C.

- Typical mold temperature : 40 – 90°C.

- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

成形加工法	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
射出成形	
納入形状	
ペレット	
特殊な特性	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
導電, 熱安定化, 光安定化	
領域別の利用可能性	
北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.