

RILSAN® BMNO TLD

PA11, MHLR, 12-010

Rilsan® BMNO TLD resin is a polyamide 11 produced from a renewable source. This natural grade is designed for injection molding.

特性	乾燥/調湿	単位	テスト基準
レオロジー特性			
メルトボリュームレイト	30 / *	cm³/10min	ISO 1133
温度	235 / *	°C	-
	455 / *	°F	
荷重	2.16 / *	kg	-
	4.76 / *	lb	
成形収縮率, 平行	1.1 / *	%	ISO 294-4, 2577
成形収縮率, 直角	1.0 / *	%	ISO 294-4, 2577
機械的特性			
引張弾性率	- / 1320	MPa	ISO 527-1/-2
	- / 191000	psi	
降伏応力	- / 41	MPa	ISO 527-1/-2
	- / 5950	psi	
降伏ひずみ	- / 5	%	ISO 527-1/-2
破壊呼びひずみ	- / >50	%	ISO 527-1/-2
ショア硬さD, 15 s	68 / *	-	ISO 868
シャルピー衝撃強さ, +23°C	- / 未破壊	kJ/m²	ISO 179/1eU
シャルピー衝撃強さ, -30°C	- / 未破壊	kJ/m²	ISO 179/1eU
ノッチ付きシャルピー衝撃強さ, +23°C	- / 8.3	kJ/m²	ISO 179/1eA
	- / 3.95	ftlb/in²	
ノッチ付きシャルピー衝撃強さ, -30°C	- / 10.5	kJ/m²	ISO 179/1eA
	- / 4.99	ftlb/in²	
熱的特性			
溶融温度, 10°C/min	189 / *	°C	ISO 11357-1/-3
荷重たわみ温度, 1.80 MPa	50 / *	°C	ISO 75-1/-2
	122 / *	°F	
荷重たわみ温度, 0.45 MPa	145 / *	°C	ISO 75-1/-2
	293 / *	°F	
ピカット軟化温度, 50°C/h 50N	160 / *	°C	ISO 306
	320 / *	°F	
線膨張係数, 平行	85 / *	E-6/K	ISO 11359-1/-2
電気的特性.			

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

RILSAN® BMNO TLD

比誘電率, 100Hz	4 / -	-	IEC 60250
比誘電率, 1MHz	3 / -	-	IEC 60250
誘電正接, 100Hz	598 / -	E-4	IEC 60250
誘電正接, 1MHz	262 / -	E-4	IEC 60250
体積抵抗率	- / 1E12	Ohm* m	IEC 62631-3-1
表面抵抗率	* / 1E14	Ohm	IEC 62631-3-2
耐電圧	- / 30 - / 762	kV/m kV/in	IEC 60243-1
耐トラッキング性	* / 600	-	IEC 60112
その他の特性.			
吸水率, 23°C, immersion, equilibrium	1.9 / *	%	ISO 62
吸湿率	0.8 / *	%	ISO 62
密度	1030 / 1030	kg/m³	ISO 1183
	1.03 / 1.03	g/cm³	

Main applications:

- Quick connectors parts

Packaging:


This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

Shelf Life:


Two years from the delivery. For any use above this limit, please refer to our technical services.

機能


粘度せん断速度.




せん断応力-せん断速度.




せん断弾性率-温度.




応力-ひずみ.




割線弾性率—ひずみ.



応力-ひずみ (等時的) 248°F



クリープ弾性率—時間. 248°F



Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 210°C / 230°C / 280°C.
- Mold temperature : 20 - 60°C
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 80-90°C.

RILSAN® BMNO TLD

成形加工法 射出成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 ペレット	
添加剤 離型剤	
特殊な特性 バイオベース, 熱安定化, 光安定化	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.