

RILSAN® CLEAR G170

PA,,MT,C12-020

Rilsan® Clear G170 is a high performance transparent polyamide resin with outstanding thermal resistance. This grade has been designed for injection molding applications.

特性	乾燥/調湿	単位	テスト基準
レオロジー特性			
メルトボリュームレイト	2 / *	cm³/10min	ISO 1133
温度	275 / *	°C	-
	527 / *	°F	
荷重	2.16 / *	kg	-
	4.76 / *	lb	
成形収縮率, 平行	1.1 / *	%	ISO 294-4, 2577
成形収縮率, 直角	1.1 / *	%	ISO 294-4, 2577
機械的特性			
引張弾性率	2100 / 2020	MPa	ISO 527-1/-2
	305000 / 293000	psi	
降伏応力	76 / 74	MPa	ISO 527-1/-2
	11000 / 10700	psi	
降伏ひずみ	8 / 9	%	ISO 527-1/-2
破壊呼びひずみ	>50 / >50	%	ISO 527-1/-2
ショア硬さD, 15 s	79 / *	-	ISO 868
シャルピー衝撃強さ, +23°C	- / 未破壊	kJ/m²	ISO 179/1eU
シャルピー衝撃強さ, -30°C	未破壊 / 未破壊	kJ/m²	ISO 179/1eU
ノッチ付きシャルピー衝撃強さ, +23°C	- / 13	kJ/m²	ISO 179/1eA
	- / 6.18	ftlb/in²	
ノッチ付きシャルピー衝撃強さ, -30°C	- / 13	kJ/m²	ISO 179/1eA
	- / 6.18	ftlb/in²	
熱的特性			
ガラス転移点, 10°C/min	168 / *	°C	ISO 11357-1/-2
	334 / *	°F	
荷重たわみ温度, 1.80 MPa	136 / *	°C	ISO 75-1/-2
	277 / *	°F	
荷重たわみ温度, 0.45 MPa	150 / *	°C	ISO 75-1/-2
	302 / *	°F	
ビカット軟化温度, 50°C/h 50N	160 / *	°C	ISO 306
	320 / *	°F	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

RILSAN® CLEAR G170

線膨張係数, 平行	70 / *	E-6/K	ISO 11359-1/-2
1.5mm厚さでの燃焼性	V-2 / *	class	IEC 60695-11-10
試験片の厚さ	1.6 / *	mm	-
	0.0630 / *	in	-
Yellow Card 可用	はい / *	-	-
酸素指数	26 / *	%	ISO 4589-1/-2
電気的特性.			
体積抵抗率	- / 1E11	Ohm* m	IEC 62631-3-1
表面抵抗率	* / 1E12	Ohm	IEC 62631-3-2
耐電圧	- / 50	kV/m	IEC 60243-1
	- / 1270	kV/in	
耐トラッキング性	* / 600	-	IEC 60112
その他の特性.			
吸水率, 23°C, immersion, equilibrium	3.8 / *	%	ISO 62
吸湿率	1.7 / *	%	ISO 62
密度	1050 / 1050	kg/m³	ISO 1183
	1.05 / 1.05	g/cm³	
光学特性			
視感透過率	91	%	ISO 13468-1, -2

Main applications:

- Coffee machine, Fuel filter container, Inner layer of fiber optic, Copper telephone cables resistant to rodents, power cables resistant to rodents.
- Note: This grade is not recommended by Arkema for usage in medical applications. For such applications Rilsan® Clear G170 MED should be used.

Packaging:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.


Shelf Life:

Two years from the delivery. For any use above this limit, please refer to our technical services.


RILSAN® CLEAR G170

機能


粘度せん断速度.




せん断応力-せん断速度.



せん断弾性率-温度.




引張弾性率-温度.




RILSAN® CLEAR G170

応力-ひずみ.



割線弾性率-ひずみ.



Injection molding conditions:

- Typical melt temperature (Min / Recommended / Max) : 270°C / 290°C / 310°C.
- Typical mold temperature : 40 - 80 °C.
- Drying time and temperature (only for bags opened for more than two hours): 4 - 6 hours at 90°C.

Extrusion conditions:

- Typical melt temperature (Min / Recommended / Max) : 270°C / 280°C / 290°C
- Drying time and temperature (only for bags opened for more than two hours): 4 - 6 hours at 90°C

成形加工法 射出成形, その他の押出成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 ペレット	
特殊な特性 透明	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.