

KYNAR®

HSV 1800

Kynar® HSV1800 is a commercial functional homopolymer of vinylidene fluoride, specifically designed to be used as a cathode binder in Lithium Ion Batteries.

Main Characteristics:

- High adhesion
- Excellent cathode slurry stability with Nickel Manganese Cobalt Active Materials
- High molecular weight
- Functional

特性	値	単位	テスト基準
レオロジー特性			
熔融粘度, 230°C, 100 s ⁻¹	80 - 85	kPoise	ASTM D3835
熱的特性			
熔融温度	161 - 167	°C	ASTM D3418
その他の特性			
密度	1780	kg/m ³	ISO 1183
	1.78	g/cm ³	
比重, 73 °F	≥ 1.78	-	ASTM D792
パウダーの特性			
Appearance	White sphero 〇 dal powder	-	Visual

Main applications:

- Battery

Slurry preparation

成形加工法	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
コーティング, 注型	
納入形状	
パウダー	
領域別の利用可能性	
北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.