

KYNAR® HSV 900

Kynar® resins are fluorinated thermoplastic homopolymers.

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties. This product is NSF/ANSI/CAN 61 certified.

特性	値	単位	テスト基準
レオロジー特性			
溶融粘度, 230°C, 100 s ⁻¹	49.5	kPoise	ASTM D3835
機械的特性			
降伏応力, 73 °F	40 - 55.2	MPa	ASTM D638
	5800 - 8000	psi	
破壊応力, 73 °F	34 - 43	MPa	ASTM D638
	4930 - 6240	psi	
破断伸び, 73 °F	50 - 250	%	ASTM D638
ショア硬さ, D, 73 °F	76 - 80	-	ASTM D2240
曲げ弾性率, 73 °F	1380 - 2210	MPa	ASTM D790
	200000 - 320000	psi	
圧縮強度, 73 °F	68.9 - 103	MPa	ASTM D695
	10000 - 15000	psi	
ノッチ付き衝撃強さ, 73 °F	0.107 - 0.32	kJ/m	ASTM D256
	2 - 6	ftlb/in	
熱的特性			
溶融温度	165	°C	ASTM D3418
酸素指数	44	%	ASTM D2863
その他の特性.			
密度	1780	kg/m³	ISO 1183
	1.78	g/cm³	
比重, 73 °F	1.77 - 1.79	-	ASTM D792
光学特性			
Refractive Index @ sodium D line	1.42	-	ASTM D542

Main applications:

- Battery
- membrane

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR®

HSV 900

成形加工法 コーティング, 注型	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 パウダー	
特殊な特性 熱安定化	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.