

PEBAX[®]

MV 1074 SA 01 MED

Polyether block amide Pebax[®] MV 1074 SA 01 MED resin is a thermoplastic elastomer made of flexible and hydrophilic polyether and rigid polyamide.

Hydrophilic Pebax[®] MV 1074 SA 01 MED resin is suitable for extrusion or coextrusion and offers excellent high moisture absorption properties in wet environments, enhancing lubricity against bodily tissue.

Pebax[®] MV 1074 SA 01 MED resin is also an inherently dissipative polymer and can be dry blended or compounded with a polymer matrix to lower the surface resistivity of the final part.

This grade offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices. Upon request, letters regarding USP Class VI compliance can be provided.

Refractive index according to an internal method is 1.502.

特性	乾燥/調湿	単位	テスト基準
機械的特性			
引張弾性率	97 / 80	MPa	ISO 527-1/-2
	14100 / 11600	psi	
50%ひずみ時応力	10 / 10	MPa	ISO 527-1/-2
	1450 / 1450	psi	
破壊ひずみ	>50 / >50	%	ISO 527-1/-2
破壊ひずみ TPE	>300 / *	%	ISO 527-1/-2
破壊応力 TPE	30 / *	MPa	ISO 527-1/-2
	4350 / *	psi	
ショア硬さD, 15 s	38 / *	-	ISO 868
シャルピー衝撃強さ, +23°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eU
シャルピー衝撃強さ, -30°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eU
ノッチ付きシャルピー衝撃強さ, +23°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eA
ノッチ付きシャルピー衝撃強さ, -30°C	未破壊 / 未破壊	kJ/m ²	ISO 179/1eA
最大応力, 平行	32 / *	MPa	ISO 527-3
	4640 / *	psi	
最大応力, 直角	34 / *	MPa	ISO 527-3
	4930 / *	psi	
最大ひずみ, 平行	500 / *	%	ISO 527-3
最大ひずみ, 直角	700 / *	%	ISO 527-3
熱的特性			
溶融温度, 10°C/min	158 / *	°C	ISO 11357-1/-3
ガラス転移点, 10°C/min	-40 / *	°C	ISO 11357-1/-2
酸素指数	19 / *	%	ISO 4589-1/-2
電気的特性			
体積抵抗率	1.5E9 / 2.5E7	Ohm* m	IEC 62631-3-1

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

PEBAX®

MV 1074 SA 01 MED

表面抵抗率	* / 3E9	Ohm	IEC 62631-3-2
耐電圧	5 / - 127 / -	kV/m kV/in	IEC 60243-1
その他の特性.			
吸湿率	1.4 / *	%	ISO 62
密度	1070 / - 1.07 / -	kg/m ³ g/cm ³	ISO 1183

Main applications:

- Breathable membranes
- Permanent antistatic additive
- Surgical tubings and garments

Packaging:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

Shelf Life:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 200°C / 240°C / 270°C.
- Typical mold temperature: 25–60°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-6 hours at 65-75°C.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 210°C / 220°C / 230°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-6 hours at 65-75°C.

成形加工法	Headquarters:
射出成形, その他の押出成形	Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
特殊な特性	
帯電防止, 熱安定化	
領域別の利用可能性	Arkema Inc. – High Performance Polymers
北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.