

RILSAMID®

AZM 23 BLACK T6LD

ISO 16396 - PA12, GF23, M1GHLR, 16-060

Rilsamid® AZM 23 BLACK T6LD resin is a fiberglass reinforced polyamide.
This black colored grade is designed for injection moulding.

特性	乾燥/調湿	単位	テスト基準
レオロジー特性			
メルトボリュームレイト	13 / *	cm³/10min	ISO 1133
温度	235 / *	°C	-
	455 / *	°F	
荷重	5 / *	kg	-
	11 / *	lb	
成形収縮率, 平行	0.2 / *	%	ISO 294-4, 2577
成形収縮率, 直角	0.4 / *	%	ISO 294-4, 2577
機械的特性			
引張弾性率	5500 / 5070	MPa	ISO 527-1/-2
	798000 / 735000	psi	
降伏応力	101 / 105	MPa	ISO 527-1/-2
	14600 / 15200	psi	
降伏ひずみ	3 / 3.5	%	ISO 527-1/-2
破壊呼びひずみ	5 / 5.2	%	ISO 527-1/-2
破壊応力	95 / 100	MPa	ISO 527-1/-2
	13800 / 14500	psi	
シャルピー衝撃強さ, +23°C	66 / 77	kJ/m²	ISO 179/1eU
	31.4 / 36.6	ftlb/in²	
シャルピー衝撃強さ, -30°C	66 / 83	kJ/m²	ISO 179/1eU
	31.4 / 39.5	ftlb/in²	
ノッチ付きシャルピー衝撃強さ, +23°C	15 / 19	kJ/m²	ISO 179/1eA
	7.14 / 9.04	ftlb/in²	
ノッチ付きシャルピー衝撃強さ, -30°C	8 / 12	kJ/m²	ISO 179/1eA
	3.81 / 5.71	ftlb/in²	
熱的特性			
溶融温度, 10°C/min	179 / *	°C	ISO 11357-1/-3
荷重たわみ温度, 1.80 MPa	165 / *	°C	ISO 75-1/-2
	329 / *	°F	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

RILSAMID[®]

AZM 23 BLACK T6LD

荷重たわみ温度, 0.45 MPa	173 / *	°C	ISO 75-1/-2
	343 / *	°F	
ビカット軟化温度, 50°C/h 50N	165 / *	°C	ISO 306
	329 / *	°F	
線膨張係数, 平行	60 / *	E-6/K	ISO 11359-1/-2
空気中の熱分解	222	°C	1% wt. loss
	432	°F	
窒素中での熱分解	223	°C	1% wt. loss
	433	°F	
電気的特性.			
比誘電率, 100Hz	5 / -	-	IEC 60250
比誘電率, 1MHz	5 / -	-	IEC 60250
誘電正接, 100Hz	1170 / -	E-4	IEC 60250
誘電正接, 1MHz	364 / -	E-4	IEC 60250
その他の特性.			
吸水率, 23°C, immersion, equilibrium	1.3 / *	%	ISO 62
吸湿率	0.5 / *	%	ISO 62
密度	1180 / 1170	kg/m ³	ISO 1183
	1.18 / 1.17	g/cm ³	

Packaging:

This grade is delivered dried in sealed packaging (25 kg bags / 450 kg rigid containers) ready to be processed

Shelf life:

Two years from the delivery.


For any use above this limit please refer to our technical services.

RILSAMID[®]


AZM 23 BLACK T6LD

機能


粘度せん断速度.




せん断応力-せん断速度.



せん断弾性率-温度.




応力-ひずみ.



RILSAMID[®]

AZM 23 BLACK T6LD

割線弾性率—ひずみ.



Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 250°C / 265°C / 280°C.
- Typical mold temperature : 40 – 90°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

成形加工法 射出成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 ペレット	
添加剤 離型剤	
特殊な特性 熱安定化, 光安定化	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.