

RILSAN® BSR 30

PA11, MHLR, 11-140, CF 30

Rilsan® BSR 30 resin is a polyamide 11 produced from a renewable source. Light and rigid, this grade is carbon fiber reinforced and designed for injection molding.

According to ASTM D6866, the biobased carbon content is measured at 62%.

特性	乾燥/調湿	単位	テスト基準
レオロジー特性			
メルトボリュームレイト	12 / *	cm³/10min	ISO 1133
温度	235 / *	°C	-
	455 / *	°F	-
荷重	5 / *	kg	-
	11 / *	lb	-
成形収縮率, 平行	0 / *	%	ISO 294-4, 2577
成形収縮率, 直角	0.6 / *	%	ISO 294-4, 2577
機械的特性			
引張弾性率	- / 16300	MPa	ISO 527-1/-2
	- / 2.36E6	psi	
破壊応力	- / 167	MPa	ISO 527-1/-2
	- / 24200	psi	
破壊ひずみ	- / 5	%	ISO 527-1/-2
ノッチ付きシャルピー衝撃強さ, +23°C	- / 20	kJ/m²	ISO 179/1eA
	- / 9.51	ftlb/in²	
ノッチ付きシャルピー衝撃強さ, -30°C	- / 12	kJ/m²	ISO 179/1eA
	- / 5.71	ftlb/in²	
熱的特性			
熔融温度, 10°C/min	188 / *	°C	ISO 11357-1/-3
その他の特性			
%Bio-Based	62	-	ASTM D6866
密度	1150 / 1150	kg/m³	ISO 1183
	1.15 / 1.15	g/cm³	

Main applications:

- Quick connectors

Packaging:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

Shelf Life:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

RILSAN®

BSR 30

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 260°C / 275°C / 290°C.
- Mold temperature : 70 - 100°C
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 80-90°C.

成形加工法 射出成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 ペレット	
特殊な特性 バイオベース, 導電	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.