

# RILSAN®

## BESN BLACK P210 TL

PA11-HIP, EHL, 22-007

Rilsan® BESN BLACK P210 TL resin is a polyamide 11 produced from a renewable source. This black grade is plasticized and designed for extrusion.

Rilsan® BESN BLACK P210 TL resin falls into the PA11-PHLY category according to DIN 73378 and fulfills all specifications according to DIN 74324, ISO 7628, NFR 12632, and SAEJ844.

The biobased carbon content of Rilsan® BESN BLACK P210 TL resin is measured at 89% according to ASTM D6866.

特性	乾燥/調湿	単位	テスト基準
<b>機械的特性</b>			
引張弾性率	- / 600	MPa	ISO 527-1/-2
	- / 87000	psi	
降伏応力	- / 32	MPa	ISO 527-1/-2
	- / 4640	psi	
降伏ひずみ	- / 31	%	ISO 527-1/-2
破壊呼びひずみ	- / >50	%	ISO 527-1/-2
シャルピー衝撃強さ, +23°C	未破壊 / 未破壊	kJ/m²	ISO 179/1eU
シャルピー衝撃強さ, -30°C	未破壊 / 未破壊	kJ/m²	ISO 179/1eU
ノッチ付きシャルピー衝撃強さ, +23°C	- / 76	kJ/m²	ISO 179/1eA
	- / 36.2	ftlb/in²	
ノッチ付きシャルピー衝撃強さ, -30°C	- / 10	kJ/m²	ISO 179/1eA
	- / 4.76	ftlb/in²	
<b>熱的特性</b>			
溶融温度, 10°C/min	184 / *	°C	ISO 11357-1/-3
荷重たわみ温度, 1.80 MPa	45 / *	°C	ISO 75-1/-2
	113 / *	°F	
荷重たわみ温度, 0.45 MPa	110 / *	°C	ISO 75-1/-2
	230 / *	°F	
<b>その他の特性</b>			
%Bio-Based	89	-	ASTM D6866
密度	1030 / 1030	kg/m³	ISO 1183
	1.03 / 1.03	g/cm³	

Main applications:

- Fluid transportation
- Tubing for use in motor vehicle

Packaging:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

Shelf Life:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018  
Source: automatically generated TDS from Material Database on 20-02-2024

# RILSAN®

## BESN BLACK P210 TL

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 250°C / 280°C.

- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

成形加工法 異形押出成形, その他の押出成形	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com  Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
納入形状 ペレット	
添加剤 滑剤, 可塑剤	
特殊な特性 バイオベース, 熱安定化, 光安定化	
領域別の利用可能性 北アメリカ, ヨーロッパ, アジア/太平洋地域, 南・中央アメリカ, 近東/アフリカ	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.