

KYNAR FLEX®

PPA 5300

Kynar Flex® 수지 는 불소화 열가소성 공중합체입니다.

Kynar Flex® PPA 5300 수지 는 폴리올레핀용 폴리머 공정 보조제(PPA)로 사용되는 특수 설계된 펠릿입니다.

Kynar Flex® PPA 5300 수지 를 200-1000ppm 레벨에서 사용하면 압출기 압력을 줄이고 표면 마감을 개선하며 다이 빌드업을 줄이고 게이지 제어를 개선할 수 있습니다.

이 제품은 또한 Kynar Flex® PPA 5301 수지 와 같이 파우더 형태로도 제공됩니다.

물성들이	값	단위	시험규격
열적 특성			
녹는점, 10°C/min	165	°C	ISO 11357-1/-3
녹는점	≤ 329	°C	ASTM D3418
기타 특성			
밀도	700	kg/m³	ISO 1183
	0.7	g/cm³	
부피 밀도	0.5 - 0.9	g/cm³	1% wt. loss

생산 공정 필름 압출, 시트 압출, 기타	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
인도 유형 과립, 가루	
지역별 검색 북아메리카 , 유럽 , 아시아 태평양 지역, 남부 및 중앙 아메리카 , 동양 및 아프리카 근역	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.