

KYNAR FLEX®

PPA 8600

Kynar Flex®树脂 是氟化热塑性塑料共聚物。

Kynar Flex® PPA 8600树脂 是一种专用球状颗粒产品，用作聚烯烃的聚合物加工助剂（PPA）。

Kynar Flex® PPA 8600 树脂 的用量为200 -1000 ppm能降低挤出机压力，提高表面光洁度，降低模头积焦，并提高厚度控制。该产品的粉末供应款为Kynar Flex® PPA 8601 树脂。

性能	价值	单位	测试标准
热性能			
熔融温度, 10°C/min	165	°C	ISO 11357-1/-3
玻璃化转变温度, 10°C/min	-40	°C	ISO 11357-1/-2
其它性能			
密度	700	kg/m³	ISO 1183
	0.7	g/cm³	
堆积密度	0.5 - 0.9	g/cm³	1% wt. loss

加工方法	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
薄膜挤出成型, 片材挤出成型, 其它挤出成型	
供货形式	
碎粒料, 粉料	
地区供应	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
北美, 欧洲, 亚太, 中南美洲, 中东/非洲	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.