

KYNAR® MG15

Kynar® 树脂 是氟化热塑性塑料均聚物。

Kynar® MG15树脂 是一种高粘度结晶态聚偏氟乙烯聚合物。这种工程聚合物的机械强度和高耐化学腐蚀性达到了出色的平衡，非常适用于持久水净化和其他应用中的微滤膜和超滤膜。

Kynar® MG15树脂 可溶于某些溶剂，而且可用于溶液加工应用。特别推荐用于中空纤维和平板膜。

Kynar® MG15 树脂 通过了 NSF、FDA和 USP 第VI 类认证，可用于饮用水、食品加工以及生物制药应用。

性能	价值	单位	测试标准
流变性能			
熔体粘度, 230°C, 100 s ⁻¹	33 - 39	kPoise	ASTM D3835
机械性能			
拉伸模量, 73 °F	1380 - 2310	MPa	ASTM D638
	200000 - 335000	psi	
屈服应力, 73 °F	44.8 - 55.2	MPa	ASTM D638
	6500 - 8000	psi	
弯曲模量, 73 °F	1380 - 2310	MPa	ASTM D790
	200000 - 335000	psi	
热性能			
熔融温度, 10°C/min	168	°C	ISO 11357-1/-3
熔点	162 - 172	°C	ASTM D3418
玻璃化转变温度, 10°C/min	-40	°C	ISO 11357-1/-2
其它性能			
吸水性	≤ 0.04	%	ASTM D570
密度	1780	kg/m³	ISO 1183
	1.78	g/cm³	
比重, 73 °F	1.77 - 1.79	-	ASTM D792
Solution Viscosity, 20°C, #3 Brookfield	≥ 1500	cps	10% NMP Solution Spindle@20 RPM Spindle Viscometer
光学特性			
Refractive Index @ sodium D line	1.42	-	ASTM D542

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR®

MG15

加工方法 浇铸成型	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
供货形式 粉料	
特殊性能 可食品接触	
地区供应 北美, 欧洲, 亚太, 中南美洲, 中东/非洲	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.