

KYNAR FLEX®

2850-00

Kynar Flex®树脂 是氟化热塑性塑料共聚物。

出色的特性：耐化学腐蚀性、耐紫外线性、高阻隔特性、高纯度、良好的机械特性和热力学特性。

Kynar Flex® 2850-00 树脂 是一种标准的粒状颗粒产品，其柔韧性低于Kynar Flex® 2800-00 树脂，但是熔点更高。在挤出应用中，适用于要求UL电线等级达到150°C的电线和电缆结构。也适用于要求UL RTI温度额定值为140°C的应用。其粉末供应形态的产品为Kynar Flex® 2851-0树脂。

[UL 黄卡](<http://iq.ul.com/ul/cert.aspx?ULID=244852>)

性能	价值	单位	测试标准
流变性能			
熔体体积流动速度	1.1	cm ³ /10min	ISO 1133
温度	230	°C	-
	446	°F	-
载荷	5	kg	-
	11	lb	-
熔融指数	3 - 8	g/10min	ASTM D1238
温度	230	°C	-
负载	12.5	kg	-
熔体粘度, 230°C, 100 s ⁻¹	23 - 27	kPoise	ASTM D3835
机械性能			
拉伸模量	1300	MPa	ISO 527-1/-2
	189000	psi	
拉伸模量, 73 °F	1030 - 1520	MPa	ASTM D638
	150000 - 220000	psi	
屈服应力	40	MPa	ISO 527-1/-2
	5800	psi	
屈服应力, 73 °F	31 - 41.4	MPa	ASTM D638
	4500 - 6000	psi	
屈服伸长率	11	%	ISO 527-1/-2
屈服伸长率, 73 °F	5 - 15	%	ASTM D638
名义断裂伸长率	>50	%	ISO 527-1/-2
断裂拉伸强度, 73 °F	27.6 - 48.3	MPa	ASTM D638
	4000 - 7000	psi	
断裂伸长率, 73 °F	30 - 200	%	ASTM D638
TABER耐磨耗性, CS 17 1000g:pad	6 - 9	mg/1000 cycles	ASTM-G195-13A

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX[®]

2850-00

肖氏硬度, D, 73 °F	70 - 75	-	ASTM D2240
弯曲模量, 73 °F	1030 - 1240	MPa	ASTM D790
	150000 - 180000	psi	
5%伸长率时弯曲强度, 73 °F	20.7 - 34.5	MPa	ASTM D790
	3000 - 5000	psi	
压缩强度, 73 °F	41.4 - 58.6	MPa	ASTM D695
	6000 - 8500	psi	
拉伸蠕变模量, 1h	508	MPa	ISO 899-1
	73700	psi	
拉伸蠕变模量, 1000h	210	MPa	ISO 899-1
	30500	psi	
简支梁缺口冲击强度, +23°C	无断裂	kJ/m ²	ISO 179/1eA
简支梁缺口冲击强度, -30°C	5	kJ/m ²	ISO 179/1eA
	2.38	ftlb/in ²	
冲击强度, 73 °F	无断裂	kJ/m	ASTM D256
梁缺口冲击强度, 73 °F	≥ 0.214	kJ/m	ASTM D256
	≥ 4	ftlb/in	
摩擦系数, 静态vs.钢, 73°F	0.26	-	ASTM D1894
摩擦系数, 动态vs.钢, 73°F	0.19	-	ASTM D1894
热性能			
熔融温度, 10°C/min	158	°C	ISO 11357-1/-3
熔点	155 - 160	°C	ASTM D3418
玻璃化转变温度, 10°C/min	-43	°C	ISO 11357-1/-2
	-45.4	°F	
玻璃化转变温度 (Tg)	-40.6 - -38.3	°C	ASTM D7028
	-41 - -37	°F	
温度额定值为	140	°C	UL RTI
	284	°F	
热变形温度, 1.80 MPa	46	°C	ISO 75-1/-2
	115	°F	
热变形温度, 264 Psi, 248 °F/hr	37.8 - 55	°C	ASTM D648
	100 - 131	°F	
热变形温度, 0.45 MPa	114	°C	ISO 75-1/-2
	237	°F	
热变形温度, 66 Psi, 248 °F/hr	60 - 75	°C	ASTM D648
	140 - 167	°F	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX[®]

2850-00

维卡软化温度, 50°C/h 50N	107	°C	ISO 306
	225	°F	
线性热膨胀系数, 平行	160	E-6/K	ISO 11359-1/-2
热释放速率, 73 °F	12.6 - 18.5	10E-5/	ASTM D696
	7 - 10.3	°C 10E-5/	
阻燃等级, 1.5mm厚	V-0	°F class	IEC 60695-11-10
测试用试样的厚度	1.5	mm	-
	0.0591	in	
Yellow Card 现存	是的	-	-
阻燃等级, 厚度h	V-0	class	IEC 60695-11-10
测试用试样的厚度	0.8	mm	-
	0.0315	in	
氧指数	43	%	ISO 4589-1/-2
氧指数	43	%	ASTM D2863
在空气中热分解	375	°C	1% wt. loss
	707	°F	
在氮气中热分解	410	°C	1% wt. loss
	770	°F	
相对热指数, 机械的	140	°C	UL 746B
	284	°F	
相对热指数, 电气	140	°C	UL 746B
	284	°F	
电性能			
相对介电常数, 100Hz	10.5	-	IEC 60250
相对介电常数, 1MHz	6.5	-	IEC 60250
电介质常数, 1 kHz	3.5 - 10.2	-	ASTM D150
介质损耗因子, 100Hz	380	E-4	IEC 60250
介质损耗因子, 1MHz	2340	E-4	IEC 60250
耗散因素, 100 kHz	0.01 - 0.22	-	ASTM D150
体积电阻率	2E12	Ohm* m	IEC 62631-3-1
体积电阻率, DC 68 °F, 65% R.H.	2.9E14 - 3.2E14	Ohm* cm	ASTM D257
表面电阻率	1E13	Ohm	IEC 62631-3-2
介电强度	21	kV/m	IEC 60243-1
	533	kV/in	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX[®]

2850-00


电介质强度, 73°F	1.3 - 1.6	kV/mil	ASTM D149
相对耐漏电起痕指数, CTI	600	-	IEC 60112
其它性能			
吸水性, 23°C, immersion, equilibrium	0.03	%	ISO 62
吸水性	0.03 - 0.05	%	ASTM D570
吸湿性	0.015	%	ISO 62
密度	1770	kg/m ³	ISO 1183
	1.77	g/cm ³	
比重, 73 °F	1.77 - 1.8	-	ASTM D792
光学特性			
Refractive Index @ sodium D line	1.42	-	ASTM D542

主要应用


- 管道系统
- 化工行业中的腐蚀防护以及内衬管
- 海上
- 电线电缆

图表

粘度 - 剪切速度




剪切应力 - 剪切速度




KYNAR FLEX®

2850-00


动态剪切模量 - 温度




应力 - 应变.



正割模量 - 应变.



比容 - 温度(PVT)



KYNAR FLEX[®]

2850-00

加工方法 异型材挤出成型, 其它挤出成型, 传递模塑成型	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
供货形式 粒料	
特殊性能 热稳定, 光稳定	
地区供应 北美, 欧洲, 亚太, 中南美洲, 中东/非洲	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.