

KYNAR FLEX®

2900-04

Kynar Flex®树脂 是氟化热塑性塑料共聚物。

Kynar Flex® 2900-04树脂

是一种粒装的半结晶态VF基共聚物。它可用于柔性电线护套等挤出应用，或者要求较高极限氧指数的阻燃和烟气应用中的注塑。

其他特性：

——优异的热稳定性

——优异的耐磨性

——极其柔韧和坚固

符合UL 910要求

性能	价值	单位	测试标准
流变性能			
熔体体积流动速度	9	cm ³ /10min	ISO 1133
温度	232	°C	-
	450	°F	-
载荷	3.8	kg	-
	8.38	lb	-
熔融指数	4 - 21	g/10min	ASTM D1238
温度	230	°C	-
负载	3.8	kg	-
熔体粘度, 230°C, 100 s ⁻¹	6 - 12	kPoise	ASTM D3835
机械性能			
拉伸模量	700	MPa	ISO 527-1/-2
	102000	psi	
拉伸模量, 73 °F	552 - 896	MPa	ASTM D638
	80000 - 130000	psi	
屈服应力	25	MPa	ISO 527-1/-2
	3630	psi	
屈服应力, 73 °F	20 - 34.5	MPa	ASTM D638
	2900 - 5000	psi	
屈服伸长率	14.5	%	ISO 527-1/-2
屈服伸长率, 73 °F	15 - 25	%	ASTM D638
名义断裂伸长率	>50	%	ISO 527-1/-2
断裂拉伸强度, 73 °F	20 - 27.6	MPa	ASTM D638
	2900 - 4000	psi	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX®

2900-04

断裂伸长率, 73 °F	100 - 300	%	ASTM D638
TABER耐摩耗性, CS 17 1000g:pad	16 - 19	mg/1000 cycles	ASTM-G195-13A
肖氏硬度, D, 73 °F	60 - 70	-	ASTM D2240
弯曲模量, 73 °F	483 - 758 70000 - 110000	MPa psi	ASTM D790
5%伸长率时弯曲强度, 73 °F	20.7 - 34.5 3000 - 5000	MPa psi	ASTM D790
压缩强度, 73 °F	31 - 41.4 4500 - 6000	MPa psi	ASTM D695
冲击强度, 73 °F	无断裂	kJ/m	ASTM D256
梁缺口冲击强度, 73 °F	0.534 - 1.07 10 - 20	kJ/m ftlb/in	ASTM D256
摩擦系数, 静态vs.钢, 73°F	0.33	-	ASTM D1894
摩擦系数, 动态vs.钢, 73°F	0.33	-	ASTM D1894
热性能			
熔融温度, 10°C/min	143	°C	ISO 11357-1/-3
熔点	140 - 145	°C	ASTM D3418
玻璃化转变温度, 10°C/min	-40	°C	ISO 11357-1/-2
玻璃化转变温度 (Tg)	-41.1 - -39.4 -42 - -39	°C °F	ASTM D7028
热变形温度, 264 Psi, 248 °F/hr	40 - 55 104 - 131	°C °F	ASTM D648
热变形温度, 66 Psi, 248 °F/hr	60 - 75 140 - 167	°C °F	ASTM D648
热释放速率, 73 °F	12.6 - 18.5 7 - 10.3	10E-5/ °C 10E-5/ °F	ASTM D696
阻燃等级, 1.5mm厚	V-0	class	IEC 60695-11-10
测试用试样的厚度	1.5 0.0591	mm in	-
Yellow Card 现存	是的	-	-
阻燃等级, 厚度h	V-0	class	IEC 60695-11-10
测试用试样的厚度	0.8 0.0315	mm in	-
氧指数	75	%	ISO 4589-1/-2

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX[®]

2900-04

氧指数	75	%	ASTM D2863
热导率	0.144 - 0.18	W/(m K)	ASTM D433
	1 - 1.25	BTU in	
比热	745 - 958	(/hr ft ² F)	DSC
	0.28 - 0.36	BTU/(l	
在空气中热分解	375	b.°F)	1% wt. loss
	707	°F	
在氮气中热分解	410	°C	1% wt. loss
	770	°F	
电性能			
电介质常数, 1 kHz	3.5 - 10.6	-	ASTM D150
耗散因素, 100 kHz	0.02 - 0.21	-	ASTM D150
体积电阻率	2E12	Ohm* m	IEC 62631-3-1
体积电阻率, DC 68 °F, 65% R.H.	2E14	Ohm* cm	ASTM D257
电介质强度, 73°F	1.3 - 1.5	kV/mil	ASTM D149
其它性能			
吸水性, 23°C, immersion, equilibrium	0.03	%	ISO 62
吸水性	0.03 - 0.05	%	ASTM D570
密度	1780	kg/m ³	ISO 1183
	1.78	g/cm ³	
比重, 73 °F	1.77 - 1.8	-	ASTM D792

地区供应	Headquarters:
北美, 欧洲, 亚太, 中南美洲, 中东/非洲	Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com

Arkema France - A French "société anonyme", registered in the Nanterre (France)
Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2018

KYNAR FLEX[®]

2900-04

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.