

KYNAR FLEX®

3120-15

Kynar Flex®树脂 是氟化热塑性塑料共聚物。

Kynar Flex® 3120-15 树脂 专门设计用于要求温度额定值为150°C并提高阻燃性和抗烟力的电线和电缆结构中。

Kynar Flex® 3120-15 树脂 易于加工，而且具有优异的物理、机械、耐热性和阻燃特性。粘度低，易于加工。

其他特性：

——优异的热稳定性

——优异的耐磨性

——氧指数极限高

——烟排放特性极低

Kynar Flex® 3120-15 树脂 符合UL 910的阻燃性和抗烟力要求。

性能	价值	单位	测试标准
流变性能			
熔体体积流动速度	4	cm ³ /10min	ISO 1133
温度	232	°C	-
	450	°F	-
载荷	3.8	kg	-
	8.38	lb	-
熔融指数	4 - 18	g/10min	ASTM D1238
温度	230	°C	-
负载	3.8	kg	-
熔体粘度, 230°C, 100 s ⁻¹	6 - 12	kPoise	ASTM D3835
机械性能			
拉伸模量	700	MPa	ISO 527-1/-2
	102000	psi	
拉伸模量, 73 °F	689 - 1170	MPa	ASTM D638
	100000 - 170000	psi	
屈服应力	27	MPa	ISO 527-1/-2
	3920	psi	
屈服应力, 73 °F	24.1 - 34.5	MPa	ASTM D638
	3500 - 5000	psi	
屈服伸长率	15	%	ISO 527-1/-2
屈服伸长率, 73 °F	10 - 20	%	ASTM D638
名义断裂伸长率	>50	%	ISO 527-1/-2

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX®

3120-15

断裂拉伸强度, 73 °F	34.5 - 48.3	MPa	ASTM D638
	5000 - 7000	psi	
断裂伸长率, 73 °F	300 - 500	%	ASTM D638
TABER耐摩耗性, CS 17 1000g:pad	16 - 19	mg/1000 cycles	ASTM-G195-13A
肖氏硬度, D, 73 °F	65 - 70	-	ASTM D2240
弯曲模量, 73 °F	621 - 827	MPa	ASTM D790
	90000 - 120000	psi	
5%伸长率时弯曲强度, 73 °F	20.7 - 34.5	MPa	ASTM D790
	3000 - 5000	psi	
压缩强度, 73 °F	31 - 41.4	MPa	ASTM D695
	4500 - 6000	psi	
简支梁缺口冲击强度, +23°C	无断裂	kJ/m ²	ISO 179/1eA
冲击强度, 73 °F	无断裂	kJ/m	ASTM D256
梁缺口冲击强度, 73 °F	无断裂	kJ/m	ASTM D256
摩擦系数, 静态vs.钢, 73°F	0.31	-	ASTM D1894
摩擦系数, 动态vs.钢, 73°F	0.3	-	ASTM D1894
热性能			
熔融温度, 10°C/min	164	°C	ISO 11357-1/-3
熔点	161 - 168	°C	ASTM D3418
玻璃化转变温度, 10°C/min	-40	°C	ISO 11357-1/-2
玻璃化转变温度 (Tg)	-41.1 - -39.4	°C	ASTM D7028
	-42 - -39	°F	
温度额定值为	150	°C	UL RTI
	302	°F	
热变形温度, 1.80 MPa	48	°C	ISO 75-1/-2
	119	°F	
热变形温度, 264 Psi, 248 °F/hr	43.3 - 54.4	°C	ASTM D648
	110 - 130	°F	
热变形温度, 0.45 MPa	65	°C	ISO 75-1/-2
	149	°F	
热变形温度, 66 Psi, 248 °F/hr	54.4 - 76.7	°C	ASTM D648
	130 - 170	°F	
热释放速率, 73 °F	12.6 - 18.5	10E-5/°C	ASTM D696
	7 - 10.3	10E-5/°F	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX®

3120-15

阻燃等级, 1.5mm厚	V-0	class	IEC 60695-11-10
测试用试样的厚度	1.5	mm	-
	0.0591	in	
Yellow Card 现存	是的	-	-
阻燃等级, 厚度h	V-0	class	IEC 60695-11-10
测试用试样的厚度	1.0	mm	-
	0.0394	in	
氧指数	95	%	ISO 4589-1/-2
氧指数	95	%	ASTM D2863
热导率	0.144 - 0.18	W/(m K)	ASTM D433
	1 - 1.25	BTU in	
比热	745 - 958	(hr ft ² / (kg K))	DSC
	0.28 - 0.36	BTU/(l b °F)	
在空气中热分解	375	°C	1% wt. loss
	707	°F	
在氮气中热分解	410	°C	1% wt. loss
	770	°F	
相对热指数, 机械的	150	°C	UL 746B
	302	°F	
相对热指数, 电气	150	°C	UL 746B
	302	°F	
电性能			
相对介电常数, 100Hz	6.7	-	IEC 60250
电介质常数, 1 kHz	3.2 - 10.2	-	ASTM D150
介质损耗因子, 100Hz	0.105	E-4	IEC 60250
耗散因素, 100 kHz	0.02 - 0.19	-	ASTM D150
体积电阻率	2E12	Ohm* m	IEC 62631-3-1
表面电阻率, 73 °F	5.9E11 - 6.1E11	Ohm per square	ASTM D257
电介质强度, 73°F	1.3 - 1.5	kV/mil	ASTM D149
其它性能			
吸水性	0.03 - 0.05	%	ASTM D570
密度	1780	kg/m ³	ISO 1183
	1.78	g/cm ³	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

KYNAR FLEX®

3120-15

比重, 73 °F

1.77 - 1.8

-

ASTM D792

加工方法 其它挤出成型	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
供货形式 粒料	
添加剂 润滑剂	
特殊性能 热稳定, 光稳定	
地区供应 北美, 欧洲, 亚太, 中南美洲, 中东/非洲	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.