

RILSAMID®

AZM 23 BLACK T6LD

PA12, MHLR, 16-060, GF23

Rilsamid® AZM 23 BLACK T6LD树脂 是一种玻纤增强聚酰胺。该黑色牌号设计用于注塑。

性能	干 / 已调节	单位	测试标准
流变性能			
熔体体积流动速度	13 / *	cm³/10min	ISO 1133
温度	235 / *	°C	-
	455 / *	°F	-
载荷	5 / *	kg	-
	11 / *	lb	-
模塑收缩率, 平行	0.2 / *	%	ISO 294-4, 2577
模塑收缩率, 垂直	0.4 / *	%	ISO 294-4, 2577
机械性能			
拉伸模量	5500 / 5070	MPa	ISO 527-1/-2
	798000 / 735000	psi	
屈服应力	101 / 105	MPa	ISO 527-1/-2
	14600 / 15200	psi	
屈服伸长率	3 / 3.5	%	ISO 527-1/-2
名义断裂伸长率	5 / 5.2	%	ISO 527-1/-2
断裂应力	95 / 100	MPa	ISO 527-1/-2
	13800 / 14500	psi	
简支梁冲击强度, +23°C	66 / 77	kJ/m²	ISO 179/1eU
	31.4 / 36.6	ftlb/in²	
简支梁冲击强度, -30°C	66 / 83	kJ/m²	ISO 179/1eU
	31.4 / 39.5	ftlb/in²	
简支梁缺口冲击强度, +23°C	15 / 19	kJ/m²	ISO 179/1eA
	7.14 / 9.04	ftlb/in²	
简支梁缺口冲击强度, -30°C	8 / 12	kJ/m²	ISO 179/1eA
	3.81 / 5.71	ftlb/in²	
热性能			
熔融温度, 10°C/min	179 / *	°C	ISO 11357-1/-3
热变形温度, 1.80 MPa	165 / *	°C	ISO 75-1/-2
	329 / *	°F	
热变形温度, 0.45 MPa	173 / *	°C	ISO 75-1/-2
	343 / *	°F	
维卡软化温度, 50°C/h 50N	165 / *	°C	ISO 306
	329 / *	°F	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

RILSAMID[®]

AZM 23 BLACK T6LD

线性热膨胀系数, 平行	60 / *	E-6/K	ISO 11359-1/-2
在空气中热分解	222	°C	1% wt. loss
	432	°F	
在氮气中热分解	223	°C	1% wt. loss
	433	°F	
电性能			
相对介电常数, 100Hz	5 / -	-	IEC 60250
相对介电常数, 1MHz	5 / -	-	IEC 60250
介质损耗因子, 100Hz	1170 / -	E-4	IEC 60250
介质损耗因子, 1MHz	364 / -	E-4	IEC 60250
其它性能			
吸水性, 23°C, immersion, equilibrium	1.3 / *	%	ISO 62
吸湿性	0.5 / *	%	ISO 62
密度	1180 / 1170	kg/m³	ISO 1183
	1.18 / 1.17	g/cm³	

Packaging:

This grade is delivered dried in sealed packaging (25 kg bags / 450 kg rigid containers) ready to be processed

Shelf life:

Two years from the delivery.


For any use above this limit please refer to our technical services.

RILSAMID[®]


AZM 23 BLACK T6LD

图表


粘度 - 剪切速度




剪切应力 - 剪切速度



动态剪切模量 - 温度




应力 - 应变.



RILSAMID®

AZM 23 BLACK T6LD

正割模量 - 应变.



Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 250°C / 265°C / 280°C.
- Typical mold temperature : 40 – 90°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

加工方法	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
注塑	
供货形式	
粒料	
添加剂	
脱模助剂	
特殊性能	
热稳定, 光稳定	
地区供应	
北美, 欧洲, 亚太, 中南美洲, 中东/非洲	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.