

RILSAN®

BESN BLACK P212 CTL

PA11-P, EHL, 22-007-CD22

Rilsan® PA 11 G BESN BLACK P212 CTL 树脂

是一种采用可再生材料制成的聚酰胺11。该黑色专门设计用于传导性多层燃料管线应用。

包装 该牌号的供货规格为干燥型密封包装（44磅袋装），可以随时加工处理。

保质期

自发货之日起2年。有关过期使用的任何事宜，请咨询我司技术服务人员。

性能	干 / 已调节	单位	测试标准
机械性能			
拉伸模量	- / 705	MPa	ISO 527-1/-2
	- / 102000	psi	
屈服应力	- / 31	MPa	ISO 527-1/-2
	- / 4500	psi	
屈服伸长率	- / 45	%	ISO 527-1/-2
名义断裂伸长率	- / >50	%	ISO 527-1/-2
肖氏硬度D, 15 s	66 / *	-	ISO 868
简支梁冲击强度, +23°C	- / 无断裂	kJ/m²	ISO 179/1eU
简支梁冲击强度, -30°C	- / 无断裂	kJ/m²	ISO 179/1eU
简支梁缺口冲击强度, +23°C	- / 无断裂	kJ/m²	ISO 179/1eA
简支梁缺口冲击强度, -30°C	- / 9	kJ/m²	ISO 179/1eA
	- / 4.28	ftlb/in²	
热性能			
熔融温度, 10°C/min	182 / *	°C	ISO 11357-1/-3
其它性能			
密度	1160 / 1160	kg/m³	ISO 1183
	1.16 / 1.16	g/cm³	

加工条件：

—推荐熔融温度（最小值/建议值/最大值）：230°C/250°C/280°C.

—干燥时间和温度（只有包装袋打开2小时以上时才有必要干燥）：4-8 小时，80-90°C.

RILSAN®

BESN BLACK P212 CTL

加工方法 异型材挤出成型, 其它挤出成型	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
供货形式 粒料	
添加剂 增塑剂	
特殊性能 生物基, 导电, 热稳定	
地区供应 北美, 欧洲, 亚太, 中南美洲, 中东/非洲	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.