

Platamid® H 2707 Pellets

Copolyamide Hot Melt Adhesive / Extrusion Applications

Platamid® H 2707 is a standard thermoplastic copolyamide hot melt adhesive available in pellet form. This medium to high melt viscosity grade is particularly suitable for manufacturing webs, mono- and multi-filaments, and films by extrusion.

Platamid® H 2707 offers a good adhesion at low fusing conditions to various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc.).

According to ASTM D6866, the biobased carbon content is measured at 20%.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	2 / *	cm ³ /10 min	ISO 1133
Temperature	160 / *	°C	-
	320 / *	°F	-
Load	2.16 / *	kg	-
	4.76 / *	lb	-
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	102 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
%Bio-Based	20	-	ASTM D6866
Density	1060 / 1060	kg/m ³	ISO 1183
	1.06 / 1.06	g/cm ³	

AVAILABLE GRADES

This grade is available:

- dried (H 2707 T)

PACKAGING

- Platamid® H 2707 T is delivered in 25 kg sealed bags.

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

RENEWABLE CARBON CONTENT

20% (according ASTM D6866)

PROCESSING Melt Spinning	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
DELIVERY FORM Pellets	
SPECIAL CHARACTERISTICS Adhesive, Bio-Based	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.