

RILSAMID®

AESN BLACK P201 TL

ISO 16396 - PA12-HIP, EGHL, C22-007

Rilsamid® AESN BLACK P201 TL resin is a black colored polyamide 12.

This grade is plasticized and designed for tube extrusion.

Rilsamid® AESN BLACK P201 TL resin falls into the PA12-PHLY category according to DIN 73378.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	5 / *	cm ³ /10 min	ISO 1133
Temperature	235 / *	°C	-
	455 / *	°F	-
Load	5 / *	kg	-
	11 / *	lb	-
MECHANICAL PROPERTIES			
Tensile Modulus	- / 540	MPa	ISO 527-1/-2
	- / 78300	psi	
Yield Stress	- / 30	MPa	ISO 527-1/-2
	- / 4350	psi	
Yield Strain	- / 22	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness, after 15 s	64 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 7	kJ/m ²	ISO 179/1eA
	- / 3.33	ftlb/in ²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	176 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1010 / 1010	kg/m ³	ISO 1183
	1.01 / 1.01	g/cm ³	

MAIN APPLICATIONS:

- Air brake
- Tubing for use in motor vehicles

PACAKAGING:

This material is delivered in sealed packaging (800 kg rigid containers) ready to be processed.

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

RILSAMID[®]

AESN BLACK P201 TL

SHELF LIFE:

Two years from date of delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature: (Min / Recommended / Max): 230°C / 250 °C / 270 °C
- Drying time and temperature (only necessary if containers opened for more than two hours): 4 - 6 hours at 80°C

PROCESSING Profile Extrusion, Other Extrusion	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
DELIVERY FORM Pellets	
ADDITIVES Lubricants, Plasticizer	
SPECIAL CHARACTERISTICS Heat Stabilized, Light Stabilized	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.