

## Platamid® H 2516 Pellets

Copolyamide Hot Melt Adhesive

**Platamid® H 2516** is a thermoplastic copolyamide hot melt adhesive available in pellet form. This fast re-crystallizing grade has been developed to manufacture hot-melt webs, nets and mono- and multi-filaments.

**Platamid® H 2516** offers a very good adhesion to all kinds of textile substrates based on native and synthetic fibers. Additionally **Platamid® H 2516** provides elastomeric properties and high water vapor transmission rate.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
<b>RHEOLOGICAL PROPERTIES</b>			
Melt Volume-Flow Rate	85 / *	cm <sup>3</sup> /10 min	ISO 1133
Temperature	160 / *	°C	-
	320 / *	°F	-
Load	2.16 / *	kg	-
	4.76 / *	lb	-
<b>THERMAL PROPERTIES</b>			
Melting Temperature, 10°C/min	108 / *	°C	ISO 11357-1/-3

## AVAILABLE GRADES

This grade is available:

- Undried with optical brightener (H 2516 FA)

## PACKAGING

Platamid® H 2516 FA is delivered in 500 kg sealed bags (GRVS) and 500 kg sealed rigid container (GRVC). These grades are ready to be processed.

## SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

<b>PROCESSING</b> Melt Spinning	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com  Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
<b>DELIVERY FORM</b> Pellets	
<b>SPECIAL CHARACTERISTICS</b> Adhesive	
<b>REGIONAL AVAILABILITY</b> North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

---

# PLATAMID®

# H 2516 PELLETS

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.